

**Study on Water Purification Using Tungsten Trioxide
Photocatalyst under Visible Light**

May 2012

Chao ZHAO

Abstract

This research investigates the application of photocatalytic purification of water under solar light irradiation through 3 aspects. Photocatalytic degradation of microcystin-LR (MC-LR) under simulated solar light using three classes of tungsten trioxide (WO₃)-based nanoparticles: CuO/WO₃, Pd/WO₃, and Pt/WO₃ was investigated. Photocatalytic activity was higher during the degradation of MC-LR with Pt/WO₃ than with Pd/WO₃ or CuO/WO₃. The pH value influenced the rate of degradation. The MC-LR degradation can be described by pseudo-first-order reaction kinetics, and the reaction rate increased with increasing light intensity. The influence of chloride ions and metal ions on the photocatalytic oxidation of MC-LR was also evaluated in this study. Chloride ion (Cl⁻) could enhance the MC-LR degradation at a concentration of 0.02 mM and could inhibit degradation at concentrations of 0.1 mM and 0.2 mM. The presence of Cu²⁺ and Fe³⁺ improved MC-LR removal from the samples. This study suggests Pt/WO₃ photocatalytic oxidation with solar light is a promising treatment for water containing MC-LR.

The photocatalytic inhibition of algal growth under solar light was investigated using *M. aeruginosa* as the model algae and Pt/WO₃ as the photocatalyst. The experiment results shows that the algal growth was successfully controlled by the Pt/WO₃ and the total MCs was also degraded to a low level. The algae cells decreased from 1.3×10^6 to 0.1×10^6 and the total MCs concentration was dropped from 624 to 100 μg/L after 6 days of photocatalytic treatment after 6 days of treatment

The comparison between photocatalytic method and electrochemical method was

investigated through the experiment of degradation of phenol. It is obvious that the reaction rate of electrochemical oxidation was much higher than that of photocatalytic oxidation. Under the optimized condition of each method, complete removal of 10mg/L phenol was achieved by photocatalytic method through 8 hours while it only took 2 hours for electrochemical method to achieve complete removal of phenol.

Table of contents

Chapter 1 Introduction	4
1.1 Advanced oxidation processes	4
1.2 Heterogeneous photocatalysis.....	4
1.3 Fundamental principles of semiconductor photocatalysis	5
1.4 History of photocatalytic materials	8
1.5 WO ₃ photocatalyst	10
1.6 Aim of present research and its significance.....	12
1.7 References.....	13
Chapter 2 Photocatalytic degradation of microcystin-LR in water using WO ₃ -based nanoparticles under simulated solar light	22
2.1 Introduction.....	22
2.2 Experimental	24
2.2.1 Chemicals and Preparation of Photocatalysts.....	24
2.2.2 Photocatalytic tests.....	25
2.2.3 Detection of Hydroxyl Radicals (•OH).....	25
2.2.4 Analysis.....	26
2.2.5 Kinetic analysis	26
2.3 Results and Discussion	27
2.3.1 Photocatalytic degradation of MC-LR with various WO ₃ -based photocatalysts.....	27
2.3.2 Photocatalytic degradation mechanism with WO ₃ -based photocatalysts	

.....	28
2.3.3 Effect of initial pH on photocatalytic degradation of MC-LR.....	29
2.3.4 Effect of light intensity on photocatalytic degradation of MC-LR and kinetic analysis.....	30
2.3.5 Effect of Cl ⁻ on photocatalytic degradation of MC-LR	31
2.3.6 Effect of metal ions on photocatalytic degradation of MC-LR	32
2.4 Conclusions.....	33
2.5 References.....	35
Chapter 3 photocatalytic inhibition of algal growth under solar light.....	49
3.1 Introduction.....	49
3.2 Materials and methods	51
3.2.1 Algal culture.....	51
3.2.2 Photocatalysts preparation and characterization.....	51
3.2.3 Photocatalytic tests.....	52
3.2.4 Analysis methods	52
3.3 Results and discussion	53
3.3.1 Characterization of photocatalyst samples.....	53
3.3.2 Photocatalytic inhibition of algal growth under solar light	53
3.3.3 Photocatalytic degradation of total MCs.....	54
3.4 Conclusions.....	55
3.5 References.....	56
Chapter 4 Comparison of the performance between photocatalytic method and electrochemical method for the degradation of phenol.....	66
4.1 Introduction.....	66

4.2 Experimental	69
4.2.1 Experiment method for electrochemical degradation of phenol.....	69
4.2.2 Experiment method for photocatalytic degradation of phenol	69
4.3 Result and discussion.....	70
4.3.1 Effect of catalyst loading on photocatalytic degradation of phenol....	70
4.3.2 Effect of light intensity on photocatalytic degradation of phenol.....	71
4.3.3 Effect of NaCl on electrochemical degradation of phenol.....	72
4.3.4 Mechanism of electrochemical oxidation of phenol.....	73
4.3.5 Effect of current density on electrochemical degradation of phenol ..	74
4.3.6 Comparison of the performance between photocatalytic method and electrochemical method	75
4.4 References.....	77
Chapter 5 Conclusions.....	88
Acknowledgements.....	91

Chapter 1 Introduction

1.1 Advanced oxidation processes

As recalcitrant organic pollutants continue to increase in air and wastewater streams, environmental laws and regulations become more stringent [1]. As a response, the development of newer eco-friendly methods of destroying these pollutants became an imperative task. Ultimately, research activities centered on advanced oxidation processes (AOPs) for the destruction of synthetic organic species resistant to conventional methods. AOPs rely on in situ generation of highly reactive radical species, mainly HO• by using solar, chemical or other forms of energy [2, 3]. The most attractive feature of AOPs is that this highly potent and strongly oxidizing radical allows the destruction of a wide range of organic chemical substrate with no selectivity.

1.2 Heterogeneous photocatalysis

Among AOPs, heterogeneous photocatalysis has proved to be of real interest as efficient tool for degrading both aquatic and atmospheric organic contaminants [4]. Heterogeneous photocatalysis involve the acceleration of photoreaction in presence of semiconductor photocatalyst. One of the major applications of heterogeneous catalysis is photocatalytic oxidation (PCO) to effect partial or total mineralisation of gas phase or liquid phase contaminants to benign substances. Even though degradation begins with a partial degradation, the term 'photocatalytic


degradation' usually refers to complete photocatalytic oxidation or photomineralisation, essentially to CO_2 , H_2O , NO_3^- , PO_4^{3-} and halide ions [5].

Photocatalysis, which was also referred to as the “Honda–Fujishima effect”, was first unfolded by the pioneering research of Fujishima and Honda [6]. These workers revealed the possibility of water splitting by photoelectrochemical cell having an inert cathode and rutile titania anode. Consequently, the application of titania photocatalysis extended to environmental frontiers. Frank and Bard [7] for the first time reported the application of TiO_2 in photocatalytic oxidation of CN^- and SO_3^{2-} in aqueous medium under sunlight. Subsequent reports of photocatalytic reduction of CO_2 by Inoue et al. [8] attracted more interest in titania photocatalysis.

1.3 Fundamental principles of semiconductor photocatalysis


Heterogeneous photocatalysis has attracted constant research since its infancy considering the high number of excellent reviews and books devoted by many researchers [9]. Despite many applications, the basic photophysical principle and physical chemistry in photocatalysis is largely the same. In the photocatalytic oxidation process, organic pollutants are destroyed in the presence of semiconductor photocatalysts (e.g., TiO_2 , ZnO), an energetic light source, and an oxidizing agent such as oxygen or air. As illustrated in Fig. 1.1, only photons with energies greater than the band-gap energy (ΔE) can result in the excitation of valence band (VB) electrons which then promote the possible reactions with organic pollutants. The absorption of photons with energy lower than ΔE or longer wavelengths usually

causes energy dissipation in the form of heat. The illumination of the photocatalytic surface with sufficient energy, leads to the formation of a positive hole (h^+) in the valence band and an electron (e^-) in the conduction band (CB). The positive hole oxidizes either the pollutant directly or water to produce hydroxyl radical $\bullet OH$, whereas the electron in the conduction band reduces the oxygen adsorbed on the photocatalyst (TiO_2). The activation of TiO_2 by UV light can be represented by the following steps.




In this reaction, h^+ and e^- are powerful oxidizing and reductive agents, respectively. The oxidative and reductive reaction steps are expressed as:

Oxidative reaction:



Reductive reaction:



Hydroxyl radical generation by the photocatalytic oxidation process is shown in the above steps. In the degradation of organic pollutants, the hydroxyl radical generated from the oxidation of adsorbed water where it is adsorbed as OH^- , is the primary oxidant, and the presence of oxygen can prevent the recombination of an

electron-hole pair. The $\bullet\text{OH}$ attacks organic compounds e.g., chlorinated aromatics, aniline and nitrophenols which result in various reaction intermediates depending on the nature of the compounds. The resulting intermediates further react with $\bullet\text{OH}$ to produce final degradation products such as CO_2 and H_2O .

The photocatalytic degradation of pollutants, when the reduction process of oxygen and the oxidation of pollutants do not advance simultaneously, there is an electron accumulation in the CB, thereby causing an increase in the rate of recombination of e^- and h^+ [10, 11]. Thus it is of paramount importance to prevent electron accumulation in efficient photocatalytic oxidation. In photocatalysis, TiO_2 is by far the most widely studied system due to its high activity, desirable physical and chemical properties, low cost, and availability. Of three common TiO_2 crystalline forms, anatase and rutile forms have been investigated extensively as photocatalysts. Anatase has been reported to be more active as a photocatalyst than rutile. Similar oxidation pathways to those of TiO_2 are confirmed in ZnO photocatalyst including the formation of $\bullet\text{OH}$ radical and the direct oxidation by photogenerated holes, etc. ZnO was reported to be as reactive as TiO_2 under concentrated sunlight, since the band-gap energy of ZnO is equal to that of TiO_2 , i.e., 3.2 eV. Some other metal oxides including CeO_2 , SnO_2 , WO_3 and CdS have also been examined for organic contaminants degradation [12-15]. At low substrate concentration, the photocatalytic degradation rate of organic compounds can be explained by a pseudo-first-order pattern, with the following equation demonstrating the relationship of C and t

$$\ln \frac{C}{C_0} = k_{\text{obs}}t \quad (1.6)$$

where k_{obs} is the apparent reaction rate constant, t the reaction time, C_0 the initial concentration of target pollutant in aqueous solution and C is the residual concentration of pollutant at time t . Different light sources such as UV lamps and solar radiation have been used in the photocatalytic degradation of various pesticides and herbicides derivatives dominant in storm water and wastewater effluent [16, 17].

1.4 History of photocatalytic materials

The discovery of water photolysis on a TiO_2 electrode by Fujishima and Honda in 1972 [6] has been recognized as the landmark event that stimulated the investigation of photonic energy conversion by photocatalytic methods, although the history of photocatalysis can be traced back to the 1960s [18-21]. Since then, intense research has been carried out on TiO_2 photocatalysis, which has been focused on understanding the fundamental principles [10,21], enhancing the photocatalytic efficiency, and expanding the scope of applications [22]. In addition to hydrogen fuel production, many other potential uses of TiO_2 photocatalysis have been identified, such as the detoxification of effluents, disinfection, superhydrophilic self-cleaning, the elimination of inorganic/organic gaseous pollutants, and the synthesis of organic fuels [23].

Unfortunately, TiO_2 is not ideal for all purposes and performs rather poorly in processes associated with solar photocatalysis. In principle, TiO_2 can utilize no more

than 5% of the total solar energy impinging on the surface of the earth due to its wide bandgap (3–3.2 eV). During the past decade, much effort has been devoted to modifying TiO₂, including energy band modulation by doping with elements such as N, C, and S [24, 25], the construction of hetero-junctions by combining TiO₂ with metals such as Pt or Pd, or other semiconductors such as NiO, RuO₂, WO₃ or CdS [26-28], and the addition of quantum dots or dyes on the TiO₂ surface for better light sensitization [29-31]. Simultaneously, the use of conventional semiconductors such as SrTiO₃, and WO₃ [32-34] in photocatalysis has been investigated in the search for possible alternatives to TiO₂. During the last decade, great efforts have been made to exploit complex metal oxides as novel photocatalytic materials, including niobates, tantalates, vandates and germanates, which contained the cations of d^0 or d^{10} electronic configurations such as In³⁺, Ga³⁺, Sb⁵⁺, Bi⁵⁺, and Ag⁺ [35]. These novel semiconductors have proved to be among the most successful photocatalysts. For example, NiO_x/In_{1-x} Ni_xTaO₄ was the first material found to catalyze overall water photolysis under visible light irradiation [36]. A number of sulfides, nitrides and oxynitrides (CdS, Ta₃N₅ and TaON are among the most promising examples) have been investigated as alternative materials for visible light or solar photocatalysis [37]. In addition to classic semiconductors, polymeric C₃N₄ was recently identified as a new photocatalyst for the production of hydrogen from water under visible light [38].

After a period of lower activity in the 1980s and 1990s, interest in photocatalysis research from a scientific and engineering viewpoint has grown exponentially. This is largely due to the rapid development of nanotechnology and advanced

characterization techniques such as TEM, EELS, and XPS, which provide great opportunities for photocatalysis to realize its anticipated potential. Through persistent effort over the past forty years, remarkable progress has been made in semiconductor photocatalysis. A number of commercial photocatalytic products, including air purifiers and self-cleaning windows, are already on the market. However, for other important applications such as the production of hydrogen and organic fuel or the fabrication of photoelectrochemical solar cells, much development is still needed before commercialization is possible.

1.5 WO₃ photocatalyst

Nanostructured tungsten trioxide (WO₃), as one of the n type semiconductors with a band gap of between 2.4 and 2.8 eV, has attracted a lot of interests in photocatalysis because of its strong adsorption within the solar spectrum (≤ 500 nm), stable physicochemical properties as well as its resilience to photo corrosions [39, 40]. Under the irradiation of visible light, photoinduced electrons and holes can be produced in the conduction band and valence band of WO₃, respectively. Its good response capabilities and physico-chemical properties make it a promising material for visible-light-driven photocatalysis.

WO₃ is a visible-light-responsive photocatalyst, but its photocatalytic activity toward organic substances is low. This is due to the fact that the conduction band level of WO₃ (+0.5V vs. NHE) is more positive than the potential for the single-electron reduction of oxygen ($O_2/O_2^- = -0.56V$ vs. NHE; $O_2/HO_2 = -0.13V$ vs. NHE) [41]. To

solve this problem, suitable modification methods were needed.

Recently, it has been reported that platinum-loaded tungsten oxide (Pt/WO₃) exhibits high photocatalytic activity for the decomposition of aliphatic compounds under visible light because the surface platinum accelerates the multielectron reduction of dioxygen [42], which has more positive potential [$E^0(\text{O}_2/\text{H}_2\text{O}_2) = +0.695 \text{ V}_{\text{NHE}}$ for two-electron reduction and $E^0(\text{O}_2/2\text{H}_2\text{O}) = +1.229 \text{ V}_{\text{NHE}}$ for four-electron reduction] than the one-electron reduction.

It is also reported that CuO can act as an effective co-catalyst for WO₃-catalyzed photodegradation of acetaldehyde to CO₂ under visible light [43]. Loading CuO on WO₃ also markedly promoted the photodegradation of other volatile organic compounds (VOCs), such as hexane, ethyl acetate, acetone, and diethyl ether. The redox potential [$(\text{EO}_2(\text{ad})/\bullet\text{O}_2^-)$] of the O₂ adsorbed on CuO might be shifted to a value more positive than the potential of the bottom of the conduction band of WO₃, or multiple-electron reduction of O₂ (such as an O₂/H₂O₂ or O₂/H₂O redox reaction) with a more-positive redox potential compared with single-electron reduction of O₂ might take place on CuO co-catalyst.

Arai et al. reported that Acetaldehyde was completely oxidized to CO₂ over a Pd/WO₃ photocatalyst under fluorescent-light irradiation in a flow-type reactor, and Pd/WO₃ was also used to completely oxidize toluene to CO₂ in a batch reactor under visible-light irradiation [41]. Pd can also precede multi-electron oxygen reduction as well as Pt.

Besides, many studies on the morphology modification of Pt/WO₃ (e.g.,

macroporous Pt/WO₃ [44], Pt/WO₃ nanotube [40], and Pt/WO₃ hollow structure [45]) and the surface modification of WO₃ (e.g., Cu(II)/WO₃ [46], and CaFe₂O₄/WO₃ [47]) have been carried out. All previous studies using modified WO₃ demonstrated the visible light photocatalytic activity through the decomposition of organic compounds.

1.6 Aim of present research and its significance

The aim of this work is to investigate the solar light induced WO₃-based photocatalytic treatment for the purification of water. Through the treatment of organic toxin, normal recalcitrant organic contaminant and algal microorganism in water, a better comprehension of heterogeneous photocatalysis in the application of wastewater treatment could be achieved. To complete this study, a lot of efforts were needed to explore the unknown world in the field of physical chemistry science, materials science and biological science. These efforts are of special environmental and economic significance for solving several environmental problems.

1.7 References

- [1] Gogate PR, Pandit AB, "A review of imperative technologies for wastewater treatment I: oxidation technologies at ambient conditions," *Advances in Environmental Research*, Vol. 8, No. 3–4, 2004, pp. 501-551.
- [2] Kudo T, Nakamura Y, Ruike A, "Development of rectangular column structured titanium oxide photocatalysts anchored on silica sheets by a wet process," *Research on Chemical Intermediates*, Vol. 29, No. 6, 2003, pp. 631-639.
- [3] Bahnemann D, "Photocatalytic water treatment: solar energy applications," *Solar Energy*, Vol. 77, No. 5, 2004, pp. 445-459.
- [4] Guillard C, Disdier J, Herrmann J-M, Lehaut C, Chopin T, Malato S, Blanco J, "Comparison of various titania samples of industrial origin in the solar photocatalytic detoxification of water containing 4-chlorophenol," *Catalysis Today*, Vol. 54, No. 2–3, 1999, pp. 217-228.
- [5] Carp O, Huisman CL, Reller A, "Photoinduced reactivity of titanium dioxide," *Progress in Solid State Chemistry*, Vol. 32, No. 1–2, 2004, pp. 33-177.
- [6] Fujishima A, Honda K, "Electrochemical Photolysis of Water at a Semiconductor Electrode," *Nature*, Vol. 238, No. 5358, 1972, pp. 37-38.
- [7] Frank SN, Bard AJ, "Heterogeneous photocatalytic oxidation of cyanide and sulfite in aqueous solutions at semiconductor powders," *The Journal of Physical Chemistry*, Vol. 81, No. 15, 1977, pp. 1484-1488.

- [8] Inoue T, Fujishima A, Konishi S, Honda K, "Photoelectrocatalytic reduction of carbon dioxide in aqueous suspensions of semiconductor powders," *Nature*, Vol. 277, No. 5698, 1979, pp. 637-638.
- [9] Augugliaro V, Litter M, Palmisano L, Soria J, "The combination of heterogeneous photocatalysis with chemical and physical operations: A tool for improving the photoprocess performance," *Journal of Photochemistry and Photobiology C: Photochemistry Reviews*, Vol. 7, No. 4, 2006, pp. 127-144.
- [10] Hoffmann MR, Martin ST, Choi W, Bahnemann DW, "Environmental Applications of Semiconductor Photocatalysis," *Chemical Reviews*, Vol. 95, No. 1, 1995, pp. 69-96.
- [11] Herrmann J-M, "Heterogeneous photocatalysis: fundamentals and applications to the removal of various types of aqueous pollutants," *Catalysis Today*, Vol. 53, No. 1, 1999, pp. 115-129.
- [12] Swarnalatha B, Anjaneyulu Y, "Studies on the heterogeneous photocatalytic oxidation of 2,6-dinitrophenol in aqueous TiO₂ suspension," *Journal of Molecular Catalysis A: Chemical*, Vol. 223, No. 1-2, 2004, pp. 161-165.
- [13] Ji P, Zhang J, Chen F, Anpo M, "Ordered Mesoporous CeO₂ Synthesized by Nanocasting from Cubic Ia3d Mesoporous MCM-48 Silica: Formation, Characterization and Photocatalytic Activity," *The Journal of Physical Chemistry C*, Vol. 112, No. 46, 2008, pp. 17809-17813.
- [14] Ji P, Zhang J, Chen F, Anpo M, "Study of adsorption and degradation of acid

orange 7 on the surface of CeO₂ under visible light irradiation," *Applied Catalysis B: Environmental*, Vol. 85, No. 3–4, 2009, pp. 148-154.

- [15] Lin CF, Wu CH, Onn ZN, "Degradation of 4-chlorophenol in TiO₂, WO₃, SnO₂, TiO₂/WO₃ and TiO₂/SnO₂ systems," *Journal of Hazardous Materials*, Vol. 154, No. 1-3, 2008, pp. 1033-1039.
- [16] Bahnemann W, Muneer M, Haque MM, "Titanium dioxide-mediated photocatalysed degradation of few selected organic pollutants in aqueous suspensions," *Catalysis Today*, Vol. 124, No. 3–4, 2007, pp. 133-148.
- [17] Lachheb H, Houas A, Herrmann J-M, "Photocatalytic Degradation of Polynitrophenols on Various Commercial Suspended or Deposited Titania Catalysts Using Artificial and Solar Light," *International Journal of Photoenergy*, Vol. 2008, No. 2008, pp.
- [18] Steinbach F, "Influence of Metal Support and Ultraviolet Irradiation on the Catalytic Activity of Nickel Oxide," *Nature*, Vol. 221, No. 5181, 1969, pp. 657-658.
- [19] Muller HD, Steinbach F, "Decomposition of Isopropyl Alcohol photosensitized by Zinc Oxide," *Nature*, Vol. 225, No. 5234, 1970, pp. 728-729.
- [20] Doerffler W, Hauffe K, "Heterogeneous photocatalysis II. The mechanism of the carbon monoxide oxidation at dark and illuminated zinc oxide surfaces," *Journal of Catalysis*, Vol. 3, No. 2, 1964, pp. 171-178.

- [21] Linsebigler AL, Lu G, Yates JT, "Photocatalysis on TiO₂ Surfaces: Principles, Mechanisms, and Selected Results," *Chemical Reviews*, Vol. 95, No. 3, 1995, pp. 735-758.
- [22] Wang R, Hashimoto K, Fujishima A, Chikuni M, Kojima E, Kitamura A, Shimohigoshi M, Watanabe T, "Light-induced amphiphilic surfaces," *Nature*, Vol. 388, No. 6641, 1997, pp. 431-432.
- [23] Roy SC, Varghese OK, Paulose M, Grimes CA, "Toward Solar Fuels: Photocatalytic Conversion of Carbon Dioxide to Hydrocarbons," *ACS Nano*, Vol. 4, No. 3, 2010, pp. 1259-1278.
- [24] Asahi R, Morikawa T, Ohwaki T, Aoki K, Taga Y, "Visible-Light Photocatalysis in Nitrogen-Doped Titanium Oxides," *Science*, Vol. 293, No. 5528, 2001, pp. 269-271.
- [25] In S, Orlov A, Berg R, García F, Pedrosa-Jimenez S, Tikhov MS, Wright DS, Lambert RM, "Effective Visible Light-Activated B-Doped and B,N-Codoped TiO₂ Photocatalysts," *Journal of the American Chemical Society*, Vol. 129, No. 45, 2007, pp. 13790-13791.
- [26] Hu C-C, Teng H, "Structural features of p-type semiconducting NiO as a co-catalyst for photocatalytic water splitting," *Journal of Catalysis*, Vol. 272, No. 1, 2010, pp. 1-8.
- [27] Li Q, Kako T, Ye J, "WO₃ modified titanate network film: highly efficient photo-mineralization of 2-propanol under visible light irradiation," *Chemical*

Communications, Vol. 46, No. 29, 2010, pp. 5352-5354.

- [28] Jang JS, Choi SH, Park H, Choi W, Lee JS, "A Composite Photocatalyst of CdS Nanoparticles Deposited on TiO₂ Nanosheets," *Journal of Nanoscience and Nanotechnology*, Vol. 6, No. 11, 2006, pp. 3642-3646.
- [29] Feng J, Han J, Zhao X, "Synthesis of CuInS₂ quantum dots on TiO₂ porous films by solvothermal method for absorption layer of solar cells," *Progress in Organic Coatings*, Vol. 64, No. 2-3, 2009, pp. 268-273.
- [30] Dibbell RS, Youker DG, Watson DF, "Excited-State Electron Transfer from CdS Quantum Dots to TiO₂ Nanoparticles via Molecular Linkers with Phenylene Bridges," *The Journal of Physical Chemistry C*, Vol. 113, No. 43, 2009, pp. 18643-18651.
- [31] Nakahira T, Inoue Y, Iwasaki K, Tanigawa H, Kouda Y, Iwabuchi S, Kojima K, Grätzel M, "Visible light sensitization of platinized TiO₂ photocatalyst by surface-coated polymers derivatized with ruthenium tris(bipyridyl)," *Die Makromolekulare Chemie, Rapid Communications*, Vol. 9, No. 1, 1988, pp. 13-17.
- [32] Wagner FT, Somorjai GA, "Photocatalytic hydrogen production from water on Pt-free SrTiO₃ in alkali hydroxide solutions," *Nature*, Vol. 285, No. 5766, 1980, pp. 559-560.
- [33] Domen K, Naito S, Soma M, Onishi T, Tamaru K, "Photocatalytic decomposition of water vapour on an NiO-SrTiO₃ catalyst," *Journal of the Chemical Society*,

Chemical Communications, Vol. No. 12, 1980, pp. 543-544.

- [34] Reiche H, Dunn WW, Bard AJ, "Heterogeneous photocatalytic and photosynthetic deposition of copper on Titanium dioxide and tungsten(VI) oxide powders," *The Journal of Physical Chemistry*, Vol. 83, No. 17, 1979, pp. 2248-2251.
- [35] Tong H, Ouyang S, Bi Y, Umezawa N, Oshikiri M, Ye J, "Nano-photocatalytic Materials: Possibilities and Challenges," *Advanced Materials*, Vol. 24, No. 2, 2012, pp. 229-251.
- [36] Zou Z, Ye J, Sayama K, Arakawa H, "Direct splitting of water under visible light irradiation with an oxide semiconductor photocatalyst," *Nature*, Vol. 414, No. 6864, 2001, pp. 625-627.
- [37] Osterloh FE, "Inorganic Materials as Catalysts for Photochemical Splitting of Water," *Chemistry of Materials*, Vol. 20, No. 1, 2007, pp. 35-54.
- [38] Wang X, Maeda K, Thomas A, Takanabe K, Xin G, Carlsson JM, Domen K, Antonietti M, "A metal-free polymeric photocatalyst for hydrogen production from water under visible light," *Nat Mater*, Vol. 8, No. 1, 2009, pp. 76-80.
- [39] Bamwenda GR, Arakawa H, "The visible light induced photocatalytic activity of tungsten trioxide powders," *Applied Catalysis a-General*, Vol. 210, No. 1-2, 2001, pp. 181-191.
- [40] Zhao ZG, Miyauchi M, "Nanoporous-walled tungsten oxide nanotubes as highly

active visible-light-driven photocatalysts," *Angewandte Chemie-International Edition*, Vol. 47, No. 37, 2008, pp. 7051-7055.

- [41] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Complete oxidation of acetaldehyde and toluene over a Pd/WO₃ photocatalyst under fluorescent- or visible-light irradiation," *Chemical Communications*, Vol. No. 43, 2008, pp. 5565-5567.
- [42] Abe R, Takami H, Murakami N, Ohtani B, "Pristine simple oxides as visible light driven photocatalysts: Highly efficient decomposition of organic compounds over platinum-loaded tungsten oxide," *Journal of the American Chemical Society*, Vol. 130, No. 25, 2008, pp. 7780-7781.
- [43] Arai T, Yanagida M, Konishi Y, Iwasaki Y, Sugihara H, Sayama K, "Promotion effect of CuO co-catalyst on WO₃-catalyzed photo degradation of organic substances," *Catalysis Communications*, Vol. 9, No. 6, 2008, pp. 1254-1258.
- [44] Sadakane M, Sasaki K, Kunioku H, Ohtani B, Ueda W, Abe R, "Preparation of nano-structured crystalline tungsten(VI) oxide and enhanced photocatalytic activity for decomposition of organic compounds under visible light irradiation," *Chemical Communications*, Vol. No. 48, 2008, pp. 6552-6554.
- [45] Zhao Z-G, Miyauchi M, "Shape Modulation of Tungstic Acid and Tungsten Oxide Hollow Structures," *The Journal of Physical Chemistry C*, Vol. 113, No. 16, 2009, pp. 6539-6546.
- [46] Irie H, Miura S, Kamiya K, Hashimoto K, "Efficient visible light-sensitive

photocatalysts: Grafting Cu(II) ions onto TiO₂ and WO₃ photocatalysts,"

Chemical Physics Letters, Vol. 457, No. 1–3, 2008, pp. 202-205.

- [47] Liu Z, Zhao Z-G, Miyauchi M, "Efficient Visible Light Active CaFe₂O₄/WO₃ Based Composite Photocatalysts: Effect of Interfacial Modification," *The Journal of Physical Chemistry C*, Vol. 113, No. 39, 2009, pp. 17132-17137.




Fig. 1.1 Basic principal of photocatalysis

Chapter 2 Photocatalytic degradation of microcystin-LR in water using WO₃-based nanoparticles under simulated solar light

2.1 Introduction

An intensification of agricultural and industrial activities resulting from an increase in population has led to eutrophication in superficial freshwater bodies and has therefore induced more frequent cyanobacteria blooms worldwide. The toxins released into freshwater by cyanobacteria are well-documented [1].

Microcystins are the most commonly occurring toxins released by cyanobacteria. Microcystins are a family of cyclic heptapeptides hepatotoxins containing the unique C₂₀ amino acid, 3-amino-9-methoxy-2,6,8-trimethyl-10-phenyldeca-4,6-dienoic acid, which is abbreviated Adda. The most abundant and frequently detected microcystin is microcystin-LR (MC-LR), which has leucine (L) and arginine (R) in the variable positions. Microcystins are strongly hepatotoxic because they disrupt protein phosphatases 1 and 2A [2], which may promote primary liver cancer and cause the death of animals and humans. The World Health Organization (WHO) has determined a provisional guideline value of 1.0 µg/L for MC-LR in drinking water.

Various water treatment processes have been evaluated to determine their efficacy in degrading these toxins because microcystins are considered a threat to human health. However, MCs are chemically stable across a range of pH values and temperatures, due to a cyclic structure [3]; consequently, traditional water treatment

processes are unsuccessful in removing MCs [4-6].

Photocatalytic oxidation is an advanced oxidation technology that has been deemed an environmentally friendly water treatment option in recent years [7-11]. When a photocatalyst is illuminated with a light of an appropriate wavelength, pairs of electrons (e^-) and electron holes (h^+) are generated on the surface of the catalyst by photons. These pairs react with oxygen and water molecules or hydroxyl groups adsorbed on the surface of the catalyst and form highly reactive oxygen species, such as hydroxyl radicals ($\bullet\text{OH}$), superoxide ions ($\bullet\text{O}_2^-$) or hydroperoxyl radicals ($\bullet\text{OOH}$) [12]. Reactive oxygen species can nonselectively oxidize a large number of organic wastes, including dyes, pesticides, bacteria and herbicides [7-9, 13]. Previous research proved that photocatalytic oxidation with TiO_2 photocatalyst could effectively destroy MCs, even at extremely high toxin concentrations [14, 15]. However, TiO_2 has a large absorption band gap (E_g) of 3.2 eV that restricts its universal use because it can only absorb UV light [16]. Conversely, with an E_g between 2.4 eV and 2.8 eV, tungsten oxide (WO_3) is a photocatalyst that absorbs visible light irradiation up to 480 nm [11]. Compared with mixed metal oxides and doped oxides, WO_3 is inexpensive to prepare and stable in acidic and oxidative conditions, which makes it a promising material for photocatalytic applications. Previous research showed that WO_3 degradation of organic species under visible light intensified in the presence of suitable co-catalysts, such as Pt, Pd and CuO [17-19]. However, there is no literature on the photocatalytic degradation of MCs under visible light with WO_3 -based catalysts.

In our study, the photocatalytic degradation of MC-LR, a model toxin, was

investigated using three types of WO_3 -based photocatalysts: CuO/WO_3 , Pd/WO_3 , and Pt/WO_3 , and simulated solar irradiation. Variations in sample parameters, such as initial pH and light intensity, were present in this study and are discussed later. Chloride ions are common in waste and natural waters, and they are important in many treatment technologies, such as breakpoint chlorination method. The presence of Cl^- can enhance the performance of advanced oxidation technologies, such as the electrochemical oxidation method [20]. Therefore, it is necessary to investigate the effect of the chloride ion on the photocatalytic degradation of MC-LR. Moreover, natural waters and industrial wastes also contain dissolved metal ions, and the redox activity of metal ions may affect the rate of photocatalytic reactions. In this study, the influence of multiple metal ions on the photocatalytic oxidation of MC-LR was evaluated.

2.2 Experimental

2.2.1 Chemicals and Preparation of Photocatalysts

MC-LR standard ($\geq 95\%$ purity; FW 995.2 g/mol) and WO_3 powder was purchased from Wako (Wako Pure Chemical Industries, Ltd., Japan). A 50-mg/L standard of toxin solution was prepared by adding 0.25 mg of solid toxin to 5 mL methanol. Sigma–Aldrich (Sigma-Aldrich Co. LLC., USA) supplied Pd powder with a surface area of 40 to 60 m^2/g and hexachloroplatinic acid ($\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$). Ishihara (Ishihara Sangyo Ltd., Japan) supplied the nanoparticle compound TiO_2 (ST-21).

The sample of CuO/WO_3 was prepared by an impregnation method using WO_3

and $\text{Cu}(\text{NO}_3)_2$ [19]. Pd/WO_3 was prepared by the mechanical mixing of Pd and WO_3 in a ceramic mortar [21]. Pt/WO_3 was prepared by a photo deposition method using WO_3 and $\text{H}_2\text{PtCl}_6 \cdot 6\text{H}_2\text{O}$ [17].

2.2.2 Photocatalytic tests

The reactor was a 6-mL vessel equipped with a magnetic stirrer. A solar lamp (XC-100B, SERIC Ltd., Japan) was used as the irradiation source, and the light intensity was measured with a photometer (LI-250A, LI-COR Inc., USA). The photoemission spectrum was measured with an optical fiber spectrometer (USB4000, Ocean Optics Inc., USA).

An aliquot of MC-LR standard solution was added to the test solution to achieve an initial concentration of 1 mg/L. A suspension with catalyst particles was transferred to the reactor containing MC-LR to obtain a final volume of 5 ml. The initial pH was adjusted with H_2SO_4 or NaOH. Before irradiation, the suspension was stirred for 60 min in the dark to equilibrate the solution. During irradiation, samples were taken and centrifuged every 30 minutes for analysis. To evaluate the efficacy of degradation of MC-LR by different photocatalysts, a set of parallel experiments were conducted using three WO_3 -based photocatalyst: Pt/WO_3 , Pd/WO_3 and CuO/WO_3 .

2.2.3 Detection of Hydroxyl Radicals ($\bullet\text{OH}$)

Photoluminescence (PL) with terephthalic acid as a probe molecule was used to detect $\bullet\text{OH}$ in the photocatalytic reaction system. Terephthalic acid reacts with $\bullet\text{OH}$ to produce highly fluorescent 2-hydroxyterephthalic acid [22].

In a beaker, a photocatalyst powder was dispersed in 20 mL of 5×10^{-4} M

terephthalic acid aqueous solution and 2×10^{-3} M NaOH. The solar lamp was used as a light source. Samples were centrifuged every 20 min for analysis.

2.2.4 Analysis

The degradation of microcystin-LR was monitored by High-performance liquid chromatography (HPLC) (Jasco-1500, Jasco, Inc., Japan) with a high-resolution diode array detector (Jasco UV-1570) set at wavelength of 238 nm. Samples were separated on a C18 column (5 m, 250 mm, 4.6 mm id) using a mobile phase of acetonitrile and Milli-Q water containing 0.01 mol/L ammonium acetate (pH 6.8; 32:68 v/v) and a flow rate of 1 mL/min. PL spectra generated by the 2-hydroxyterephthalic acid were measured on a Hitachi F-4500 fluorescence spectrophotometer set at a wavelength of 315 nm. The pH values of the solutions were measured with a pH meter (TES-1380, TES Co., Taiwan).

2.2.5 Kinetic analysis

Photocatalytic oxidation reaction reactions have been modeled with a pseudo-first-order kinetic equation (Eq. 2.1).

$$\ln (C_0/C_t) = kt \quad (2.1)$$

where C_0 (mg/L) is the initial concentration of MC-LR after dark adsorption, and C_t (mg/L) is the concentration of MC-LR over reaction time t (min).

2.3 Results and Discussion

2.3.1 Photocatalytic degradation of MC-LR with various WO₃-based photocatalysts

As shown in Fig. 2.1, the concentration of MC-LR was virtually unchanged after 3 h of irradiation when there was no photocatalyst in the solution, thereby indicating MC-LR was stable under solar irradiation. After 3 h of irradiation, 19% of MC-LR was removed from a solution with only TiO₂ added, and 24% of MC-LR was removed from a solution in which only WO₃ was added. The modified WO₃-based catalysts CuO/WO₃ and Pd/WO₃ achieved 31% and 43% MC-LR removal, respectively, with 3 h of irradiation. Over 81% of MR-LR was degraded by the Pt/WO₃ composite within 90 min. Furthermore, the removal efficacy was 100% when the contact time was lengthened to 180 min.


Poor MC-LR removal efficiency by a solution containing only TiO₂ was attributable to the light source. The simulated solar lamp used in this experiment emitted light with wavelengths greater than 400 nm (Fig. 2.2), and the TiO₂ excitation range is less than 390 nm [16]. The low photocatalytic activity of pure WO₃ is because the conduction band level of WO₃ (+0.5V vs. NHE) is more positive than the potential for the single-electron reduction of oxygen (O₂/O₂⁻ = -0.56V vs. NHE; O₂/HO₂ = -0.13V vs. NHE) [18]. Without co-catalysts, the high conduction band of WO₃ restricts the compound's activity with an organic compound [11].

The WO₃-based photocatalysts results from this study are supported by previous research. Arai et al. reported that the activity of Pd/WO₃ was more than twice the

activity of CuO/WO₃ in the degrading acetaldehyde, and the performance of Pt/WO₃ was better than the performance of CuO/WO₃ in the degradation of CH₃CHO [18, 19].

2.3.2 Photocatalytic degradation mechanism with WO₃-based photocatalysts

CuO, Pd, and Pt, which are co-catalysts for WO₃-induced photocatalytic reactions, can promote O₂ reduction in a multi-electron process [18, 23]. In a photocatalytic reaction, the following chain reactions have been postulated [12]:



Several highly reactive oxygen species, such as $\bullet\text{OH}$, $\text{HOO}\bullet$ and $\text{O}_2\bullet^{-}$, are generated through the reduction of O₂ to oxidized organic compounds. Accordingly, organic compounds could be effectively degraded by WO₃ in the presence of a co-catalyst.

Photocatalytic degradation of MC-LR was initiated by the attack of hydroxyl radical on the conjugated diene structure of Adda [24], thereby indicating the primary

reactive species in MC-LR degradation was the hydroxyl radical. Kim et al. proved that the deposition of Pt on WO_3 facilitates the generation of OH radicals under visible light [25], and our experiments confirmed this phenomenon using photoluminescence (PL). Fig. 2.3 shows the spectra observed during irradiation of the Pt/ WO_3 sample. At approximately 425 nm, PL intensity gradually increased with an increase in irradiation time, thereby suggesting that OH radicals are formed on the photocatalyst-water interface via photocatalytic reactions [22, 26].

Fig. 2.4 shows the plots of PL intensity for the three types of WO_3 -based photocatalysts at 425 nm as a function of irradiation time. The results showed that the PL intensities by induced by simulated solar light in terephthalic acid solutions were linearly related to an increase in irradiation time. The number of OH radicals produced on the surface of the photocatalyst was proportionate to the irradiation time and obeyed zero-order reaction rate kinetics [22, 26]. Furthermore, the slopes of the lines in Fig. 2.4 describe the generation rate of OH radicals. The rate of OH radical production on the surface of Pt/ WO_3 is greater than the rate of production on the surfaces of Pd/ WO_3 or CuO/ WO_3 . Without a co-catalyst, WO_3 could only generate a small number of OH radicals with solar-light irradiation. Because the photocatalytic degradation of MC-LR was initiated by an OH radical [24], Pt/ WO_3 is particularly effective in the photocatalytic degradation of MC-LR because of a higher OH radical production rate. Because of its efficacy, we used Pt/ WO_3 in subsequent experiments.

2.3.3 Effect of initial pH on photocatalytic degradation of MC-LR

The pH affects the surface condition of catalysts and MC-LR and the generation

of hydroxyl radical in hydroxylation reactions. After 180 min of irradiation, the removal of MC-LR was 89%, 100% and 77% with pH values of 3, 6 and 10, respectively (Fig. 2.5).

Although the degradation of MC-LR was initiated by the attack of hydroxyl radical [24], the number of $\bullet\text{OH}$ ions should be lower at an acidic pH because hydronium ions favor the presence of an electron hole (Eq. 2.9) [27]. At low pH, MC-LR degradation would be adversely affected due to the lack of OH^- ions. The initial pH was adjusted by H_2SO_4 , but Liang et al. reported that SO_4^{2-} ions have an adverse effect on the photocatalytic degradation rate [28]. Given the evidence, we can explain the lower efficiency observed in our experiment at acid pH.

The point of zero zeta-potential (PZZP) for WO_3 occurs at approximately pH 2, and WO_3 particles are negatively charged when the pH of a solution is greater than 2[25]. At pH values between 3 and 12, the carboxylic groups of MC-LR are ionized, and the molecule is negatively charged [29]. In basic conditions, negatively charged WO_3 molecules repel MC-LR and inhibit interactions between the toxins and the catalysts. Fewer interactions result in lower photocatalytic activity and a lower degradation rate. Our results are consistent with a study by Lawton et al. in which the reaction rate of photocatalytic degradation of MC-LR by TiO_2 was lowest at pH 10 [30].

2.3.4 Effect of light intensity on photocatalytic degradation of MC-LR and kinetic analysis

Light intensity influences photocatalytic activity and the energy of the

photocatalytic system. As shown in Fig. 2.6, the curves between $\ln(C_0/C_t)$ and irradiation time were consistent with first-order kinetics and had R^2 values greater than or equal to 0.99.

As expected, the photocatalytic rate constant (k) increased from 0.0149 to 0.0248 as light intensity increased from 0.2 mW/cm² to 0.8 mW/cm². As light intensity increases, the solution contains more photons and more hydroxyl radicals, and the rate of MC-LR photocatalytic degradation increases.

2.3.5 Effect of Cl⁻ on photocatalytic degradation of MC-LR

NaCl was added into the reaction solution at different concentrations, but the other experimental conditions were unchanged. The results are shown in Fig. 2.7. Without Cl⁻, 88% of MC-LR was removed after 120 min of irradiation. However, the removal efficacy increased to 94% when Cl⁻ concentration was 0.02 mM. Conversely, the removal ratio decreased to 79% and 74% when the Cl⁻ concentrations were 0.1 mM and 0.2 mM, respectively. The results indicate that lower concentrations of Cl⁻ could enhance the degradation of toxins, but higher concentrations of Cl⁻ could inhibit degradation. Moreover, the inhibition effect was stronger at higher concentrations of Cl⁻.

In the photocatalytic process, electrons produced on the surface of the catalyst reduced O₂ molecules to •O₂⁻ radicals (Eq. 2.3), and the electron hole oxidized Cl⁻ ions to form Cl radicals (•Cl) [31, 32].



Cl radicals are oxidants that can degrade organic species. Guo, J., et al. reported

that Cl^- absorbed on TiO_2 molecules promoted the oxidation rate of propylene [33]. However, Cl^- can also scavenge hydroxyl radicals because the reaction between $\text{HO}\cdot$ and Cl^- to form Cl_2 occurs quickly, and the activity of $\cdot\text{Cl}$ was lower than that of $\cdot\text{OH}$ [28]. Consequently, when Cl^- concentration increased to the point of excess, the radical began to scavenge $\cdot\text{OH}$ preferentially at a rate that decreased photocatalytic degradation of MC-LR.

2.3.6 Effect of metal ions on photocatalytic degradation of MC-LR

In this study, $\text{Cu}(\text{NO}_3)_2$ and $\text{Fe}(\text{NO}_3)_3$ were added to reaction solutions at a concentration of 0.2 mM to investigate their effect on photocatalytic degradation of MC-LR (Fig. 2.8). The addition of Cu^{2+} and Fe^{3+} to solution enhanced the degradation of MC-LR. The amount of MC-LR removed from solution after 2 h of irradiation increased from 87% to 99% in the presence of 0.2 mM Cu^{2+} , and removal increased from 87% to 94% in the presence of 0.2 mM Fe^{3+} .


In photocatalytic degradation, an important factor that greatly affects the reaction rate is the separation of photo-excited electrons and holes. Low concentrations of liquid-phase O_2 cannot efficiently access photo-excited electrons because photo-excited holes react with organic substances, and photo-excited electrons are consumed through reduction of O_2 (Eq. 2.3) [12], Low photocatalytic activity in the liquid phase is attributable to the fast recombination of excess electrons and electron holes. Metal ions can act as a scavenger of the excess photogenerated electrons. The consumption of electrons was achieved by the reduction of Cu^{2+} and Fe^{3+} .





The reaction between metal ions and e^- reduced the number of undesirable electron hole combinations and increased the rate of $\text{HO}\cdot$ formation (Eq. 2.11 – Eq. 2.12) [34].

Furthermore, the metal ions can use H_2O_2 generated in Eq. 2.7 in a photo-Fenton reaction.



The consumed form of an ion can be regenerated through Eq. 2.13 and Eq. 2.14 with photo-excited electrons, and additional $\text{HO}\cdot$ is produced and subsequently promotes the degradation of MC-LR [35, 36]. Other researchers have reported on the use of metal ions for the enhancement of photocatalytic reaction efficiency. Arai et al. used $\text{Fe}^{3+}/\text{Fe}^{2+}$ redox for the photodegradation of organic substances with WO_3 photocatalysts [37]. Beydoun et al. reported Cu^{2+} enhanced the photocatalytic degradation of sucrose [38].

2.4 Conclusions

Under simulated solar irradiation, WO_3 degrades MC-LR more effectively in the presence of co-catalyst compared to solutions with only TiO_2 or WO_3 . The highest rate of MC-LR removal occurred in solutions containing Pt/ WO_3 . Specifically, 1 mg/L of MC-LR was removed after 3 h of irradiation by 100 mg/L of Pt/ WO_3 . A neutral pH, such as a pH of 6, improved the efficacy of toxin removal. Analysis of

reaction kinetics indicated that photocatalytic MC-LR degradation followed pseudo-first-order reaction kinetics, and the reaction rate increased with an increase in light intensity. Investigation of the effect of coexistent ions on the photocatalytic oxidation of MC-LR indicated that Cl^- could enhance the MC-LR degradation at concentrations lower than 0.02 mM and inhibit degradation at concentrations of 0.1 mM and 0.2 mM. The presence of Cu^{2+} or Fe^{3+} can improve MC-LR removal. This treatment method is a promising method for enhancing the treatment of refractory organic compounds.

2.5 References

- [1] Al Momani F, Smith DW, El-Din MG, "Degradation of cyanobacteria toxin by advanced oxidation processes," *Journal of Hazardous Materials*, Vol. 150, No. 2, 2008, pp. 238-249.
- [2] Honkanen RE, Zwiller J, Moore RE, Daily SL, Khatra BS, Dukelow M, Boynton AL, "Characterization of microcystin-LR, a potent inhibitor of type-1 and type-2A protein phosphatases," *Journal of Biological Chemistry*, Vol. 265, No. 32, 1990, pp. 19401-19404.
- [3] Watanabe MF, Carmichael WW: **Toxic microcystis**: CRC Press; 1996.
- [4] Vasconcelos VM, Pereira E, "Cyanobacteria diversity and toxicity in a Wastewater Treatment Plant (Portugal)," *Water Research*, Vol. 35, No. 5, 2001, pp. 1354-1357.
- [5] Himberg K, Keijola AM, Hiisvirta L, Pyysalo H, Sivonen K, "The effect of water treatment processes on the removal of hepatotoxins from *Microcystis* and *Oscillatoria* cyanobacteria: A laboratory study," *Water Research*, Vol. 23, No. 8, 1989, pp. 979-984.
- [6] Takenaka S, Tanaka Y, "Behavior of microcystins and its decomposition product in water treatment process," *Chemosphere*, Vol. 31, No. 7, 1995, pp. 3635-3641.
- [7] Shifu C, Gengyu C, "Photocatalytic degradation of organophosphorus pesticides using floating photocatalyst $\text{TiO}_2 \cdot \text{SiO}_2$ /beads by sunlight," *Solar Energy*, Vol. 79,

No. 1, 2005, pp. 1-9.

- [8] Sharon M, Pal B, Kamat DV, "Photocatalytic Killing of Pathogenic Bacterial Cells Using Nanosize Fe_2O_3 and Carbon Nanotubes," *Journal of Biomedical Nanotechnology*, Vol. 1, No. 3, 2005, pp. 365-368.
- [9] Canle M, Fernandez MI, Rodriguez S, Santaballa JA, Steenken S, Vulliet E, "Mechanisms of direct and TiO_2 -photocatalysed UV degradation of phenylurea herbicides," *Chemphyschem*, Vol. 6, No. 10, 2005, pp. 2064-2074.
- [10] Arai T, Yanagida M, Konishi Y, Iwasaki Y, Sugihara H, Sayama K, "Efficient complete oxidation of acetaldehyde into CO_2 over $\text{CuBi}_2\text{O}_4/\text{WO}_3$ composite photocatalyst under visible and UV light irradiation," *Journal of Physical Chemistry C*, Vol. 111, No. 21, 2007, pp. 7574-7577.
- [11] Miyauchi M, "Photocatalysis and photoinduced hydrophilicity of WO_3 thin films with underlying Pt nanoparticles," *Physical Chemistry Chemical Physics*, Vol. 10, No. 41, 2008, pp. 6258-6265.
- [12] Gaya UI, Abdullah AH, "Heterogeneous photocatalytic degradation of organic contaminants over titanium dioxide: A review of fundamentals, progress and problems," *Journal of Photochemistry and Photobiology C-Photochemistry Reviews*, Vol. 9, No. 1, 2008, pp. 1-12.
- [13] Genc N, "Photocatalytic oxidation of a reactive azo dye and evaluation of the biodegradability of photocatalytically treated and untreated dye," *Water Sa*, Vol. 30, No. 3, 2004, pp. 399-405.

- [14] Lawton LA, Robertson PKJ, Cornish B, Jaspars M, "Detoxification of microcystins (cyanobacterial hepatotoxins) using TiO₂ photocatalytic oxidation," *Environmental Science & Technology*, Vol. 33, No. 5, 1999, pp. 771-775.
- [15] Liu I, Lawton LA, Bahnemann DW, Robertson PKJ, "The photocatalytic destruction of the cyanotoxin, nodularin using TiO₂," *Applied Catalysis B-Environmental*, Vol. 60, No. 3-4, 2005, pp. 245-252.
- [16] Zhao ZG, Miyauchi M, "Nanoporous-walled tungsten oxide nanotubes as highly active visible-light-driven photocatalysts," *Angewandte Chemie-International Edition*, Vol. 47, No. 37, 2008, pp. 7051-7055.
- [17] Abe R, Takami H, Murakami N, Ohtani B, "Pristine simple oxides as visible light driven photocatalysts: Highly efficient decomposition of organic compounds over platinum-loaded tungsten oxide," *Journal of the American Chemical Society*, Vol. 130, No. 25, 2008, pp. 7780-7781.
- [18] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Complete oxidation of acetaldehyde and toluene over a Pd/WO₃ photocatalyst under fluorescent- or visible-light irradiation," *Chemical Communications*, Vol. No. 43, 2008, pp. 5565-5567.
- [19] Arai T, Yanagida M, Konishi Y, Iwasaki Y, Sugihara H, Sayama K, "Promotion effect of CuO co-catalyst on WO₃-catalyzed photo degradation of organic substances," *Catalysis Communications*, Vol. 9, No. 6, 2008, pp. 1254-1258.
- [20] Li L, Liu Y, "Ammonia removal in electrochemical oxidation: Mechanism and

- pseudo-kinetics," *Journal of Hazardous Materials*, Vol. 161, No. 2-3, 2009, pp. 1010-1016.
- [21] Liu Y, Ohko Y, Zhang R, Yang Y, Zhang Z, "Degradation of malachite green on Pd/WO₃ photocatalysts under simulated solar light," *Journal of Hazardous Materials*, Vol. 184, No. 1-3, 2010, pp. 386-391.
- [22] Ishibashi K-i, Fujishima A, Watanabe T, Hashimoto K, "Detection of active oxidative species in TiO₂ photocatalysis using the fluorescence technique," *Electrochemistry Communications*, Vol. 2, No. 3, 2000, pp. 207-210.
- [23] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Reaction Mechanism and Activity of WO₃-Catalyzed Photodegradation of Organic Substances Promoted by a CuO Cocatalyst," *Journal of Physical Chemistry C*, Vol. 113, No. 16, 2009, pp. 6602-6609.
- [24] Liu I, Lawton LA, Robertson PKJ, "Mechanistic studies of the photocatalytic oxidation of microcystin-LR: An investigation of byproducts of the decomposition process," *Environmental Science & Technology*, Vol. 37, No. 14, 2003, pp. 3214-3219.
- [25] Kim J, Lee CW, Choi W, "Platinized WO₃ as an Environmental Photocatalyst that Generates OH Radicals under Visible Light," *Environmental Science & Technology*, Vol. 44, No. 17, 2010, pp. 6849-6854.
- [26] Xiao Q, Si Z, Zhang J, Xiao C, Tan X, "Photoinduced hydroxyl radical and photocatalytic activity of samarium-doped TiO₂ nanocrystalline," *Journal of*

Hazardous Materials, Vol. 150, No. 1, 2008, pp. 62-67.

- [27] Ellselami L, Vocanson F, Dappozze F, Puzenat E, Paisse O, Houas A, Guillard C, "Kinetic of adsorption and of photocatalytic degradation of phenylalanine effect of pH and light intensity," *Applied Catalysis a-General*, Vol. 380, No. 1-2, 2010, pp. 142-148.
- [28] Liang H-c, Li X-z, Yang Y-h, Sze K-h, "Effects of dissolved oxygen, pH, and anions on the 2,3-dichlorophenol degradation by photocatalytic reaction with anodic TiO₂ nanotube films," *Chemosphere*, Vol. 73, No. 5, 2008, pp. 805-812.
- [29] Antoniou MG, Shoemaker JA, de la Cruz AA, Dionysiou DD, "LC/MS/MS structure elucidation of reaction intermediates formed during the TiO₂ photocatalysis of microcystin-LR," *Toxicon*, Vol. 51, No. 6, 2008, pp. 1103-1118.
- [30] Lawton LA, Robertson PKJ, Cornish B, Marr IL, Jaspars M, "Processes influencing surface interaction and photocatalytic destruction of microcystins on titanium dioxide photocatalysts," *Journal of Catalysis*, Vol. 213, No. 1, 2003, pp. 109-113.
- [31] Munuera G, Navio A, Soria J, Gonzalez-elipe AR: **Photo-Adsorption of Oxygen on Chlorinated TiO₂ Surfaces; A Possible Way to Photo-Oxy-Chlorinations.** In: *Studies in Surface Science and Catalysis*. Edited by Seiyama T, Tanabe K, Volume 7, Part 2: Elsevier; 1981: 1185-1197.
- [32] Kutsuna S, Ebihara Y, Nakamura K, Ibusuki T, "Heterogeneous photochemical reactions between volatile chlorinated hydrocarbons (trichloroethene and

tetrachloroethene) and titanium dioxide," *Atmospheric Environment Part A General Topics*, Vol. 27, No. 4, 1993, pp. 599-604.

- [33] Guo J, Mao L, Zhang J, Feng C, "Role of Cl⁻ ions in photooxidation of propylene on TiO₂ surface," *Applied Surface Science*, Vol. 256, No. 7, 2010, pp. 2132-2137.
- [34] Ward MD, Bard AJ, "Photocurrent enhancement via trapping of photogenerated electrons of titanium dioxide particles," *The Journal of Physical Chemistry*, Vol. 86, No. 18, 1982, pp. 3599-3605.
- [35] Okamoto K, Yamamoto Y, Tanaka H, Tanaka M, Itaya A, "Heterogeneous Photocatalytic Decomposition of Phenol over TiO₂ Powder," *Bulletin of the Chemical Society of Japan*, Vol. 58, No. 7, 1985, pp. 2015-2022.
- [36] Wei T-Y, Wan C-c, "Kinetics of photocatalytic oxidation of phenol on TiO₂ surface," *Journal of Photochemistry and Photobiology A: Chemistry*, Vol. 69, No. 2, 1992, pp. 241-249.
- [37] Arai T, Yanagida M, Konishi Y, Sugihara H, Sayama K, "Utilization of Fe³⁺/Fe²⁺ redox for the photodegradation of organic substances over WO₃ photocatalyst and for H₂ production from the electrolysis of water," *Electrochemistry*, Vol. 76, No. 2, 2008, pp. 128-131.
- [38] Beydoun D, Tse H, Amal R, Low G, McEvoy S, "Effect of copper(II) on the photocatalytic degradation of sucrose," *Journal of Molecular Catalysis a-Chemical*, Vol. 177, No. 2, 2002, pp. 265-272.




Fig. 2.1 The effect of catalysts on the efficiency of photocatalytic degradation of MC-LR. Experimental conditions: MC-LR concentration of 1 mg/L, catalyst concentration of 100 mg/L and simulated solar light intensity of 0.4 mW/cm².




Fig. 2. 2 The photoemission spectrum of the light source.




Fig. 2.3 PL spectral changes observed during irradiation of the Pt/WO₃ sample. Experimental conditions: NaOH concentration of 2×10^{-3} M, terephthalic acid concentration of 5×10^{-4} M, Pt/WO₃ concentration of 200 mg/L and simulated solar light intensity of 0.4 mW/cm^2 .




Fig. 2.4 PL intensity at 42 three WO₃-based photocatalysts and one WO₃ photocatalysts as a function of irradiation time. Experimental conditions: NaOH concentration of 2×10^{-3} M, terephthalic acid concentration of 5×10^{-4} M, catalyst concentration of 200 mg/L and simulated solar light intensity of 0.4 mW/cm^2 .




Fig. 2.5 Efficiency of photocatalytic degradation of MC-LR as a function of initial pH. Experimental conditions: MC-LR concentration of 1 mg/L, Pt/WO₃ concentration of 100 mg/L and simulated solar light intensity of 0.4 mW/cm².




Fig. 2.6 Efficiency of photocatalytic degradation of MC-LR as a function of light intensity. Experimental conditions: MC-LR concentration of 1 mg/L and Pt/WO₃ concentration of 100 mg/L




Fig. 2.7 Efficiency of photocatalytic degradation of MC-LR as a function Cl⁻ concentration. Experimental conditions: MC-LR concentration of 1 mg/L, Pt/WO₃ concentration of 100 mg/L and simulated solar light intensity of 0.4 mW/cm².




Fig. 2.8 The effect of 0.2 mM of metal ions on the efficiency of photocatalytic degradation of MC-LR. Experimental conditions: MC-LR concentration of 1 mg/L, Pt/WO₃ concentration of 100 mg/L and simulated solar light intensity of 0.4 mW/cm².

Chapter 3 photocatalytic inhibition of algal growth under solar light

3.1 Introduction

Cyanobacteria (blue-green algae) are photoautotrophic gram-negative bacteria that are common members of the freshwater phytoplankton community in surface waters [1]. They are considered to be a great threaten to the drinking water quality because of their ability to produce toxins and odors. The drinking water contaminated with toxic cyanobacteria could cause the death of the domestic and wild animals and the cases of human illness [2, 3]. To minimize the threat, removal of cyanobacteria has been conducted by applying physical, chemical and biological methods such as flocculation, sedimentation, floatation, and filtration technologies. However, many problems such as high cost, producing a large amount of algae sludge, and complexity of the treatment process became the hurdle when those technologies were applied to practical use. Therefore, the development of a new sustainable technology for the control of cyanobacteria is strongly demanded.

The antimicrobial activity of photocatalytic reaction by TiO_2 was first demonstrated by Matsunaga and coworkers [4], since then, photocatalysis has been shown to be capable of killing a wide range of organisms including Gram-negative and Gram-positive bacteria, including endospores, fungi, algae, protozoa and viruses, and has also been shown to be capable of inactivating prions [5-7]. Moreover recently works also reported that TiO_2 -photocatalysis has the ability to inhibit the growth of

the filamentous algae, *Oedogonium* and *Cladophora* [8, 9]. However, TiO_2 has a large absorption band gap (E_g) of 3.2 eV that restricts its universal use because it can only absorb UV light which occupies only 3-5% of the solar spectrum [10]. From the perspective of solar light utilization, many researchers have done a lot of works to enhance the photocatalytic efficiency and visible light utilization of TiO_2 by modification methods, including anionic or cationic impurity doping [11-13], sensitization [14] and combination with smaller-bandgap semiconductors [15]. Nevertheless, the problems including complex modifying processes and low stability of the as-prepared samples were raised and prevent the further application of TiO_2 .

Compared to TiO_2 , with an E_g between 2.4 eV and 2.8 eV, tungsten oxide (WO_3) is a photocatalyst that absorbs visible light irradiation up to 480 nm [11]. Compared with mixed metal oxides and doped oxides, WO_3 is inexpensive to prepare and stable in acidic and oxidative conditions, which makes it a promising material for photocatalytic applications. Previous research showed that WO_3 degradation of organic species under visible light intensified in the presence of suitable co-catalysts, such as Pt [16-18]. However, there is no literature on the Photocatalytic inhibition of the algal growth under visible light with WO_3 -based catalysts.

In our study, platinum was chosen as the cocatalyst to modify WO_3 . It has been confirmed that Pt/ WO_3 could perform well in photocatalytic degradation of organic substances under visible light irradiation [19]. *Microcystis aeruginosa* (*M. aeruginosa*) was selected as test species, for it is the most common blue-green algae and easily causes eutrophication.

3.2 Materials and methods

3.2.1 Algal culture

M. aeruginosa was obtained from National Institute for Environment Studies (NIES) (Ibaraki, Japan), The composition of the MA medium used in algal growth tests was listed in Table 3.1. 1L of MA medium was added to a 3L conical flask and was autoclaved at 121°C for 20 min. The cultivation was carried out in the cultivating box with illumination for 10 days. The continuous light was provided by a fluorescence lamp with an automated 12 h/12 h light/dark cycle. The light intensity during the light phase was 1500 lx. The temperature was controlled at 25±1 °C.

3.2.2 Photocatalysts preparation and characterization

Pt-loaded WO₃ sample (Pt/WO₃) was prepared by a photo deposition method [18]. An aqueous suspension containing the particulate WO₃ and H₂PtCl₆•6H₂O was exposed to visible light ($\lambda > 400$ nm) provided by a 300 W Xe lamp (LX-300F, Cermax, CA) fitted with a cutoff filter (L-42, HOYA, Japan). After 2 h of irradiation, methanol (10 vol%) was added and the suspension exposed to further irradiation for 2 h. The prepared sample was collected by centrifugation and washed twice with Milli-Q water and finally dried at 105 °C for 2 h. The prepared sample was characterized. UV-visible spectrum of the sample was recorded on a spectrophotometer (UV-2550, Shimadzu Co. Ltd., Japan). X-ray powder diffraction (XRD) measurement was carried out by using an X-ray diffractometer (Rigaku Smartlab).

3.2.3 Photocatalytic tests

Photocatalytic inhibition of *M. aeruginosa* was carried out in a 200-mL beaker equipped with a magnetic stirrer. The irradiation source was the same solar lamp with an automated 12 h/12 h light/dark cycle. All the experiment equipments were placed in a clean bench to prevent the interference of dust and microorganism brought by air. 150ml of algal solution and a suspension with catalyst particles were added to the beaker for irradiation. Samples were taken every 2 days for analysis. The experiment apparatus are shown in Fig. 3.1.

3.2.4 Analysis methods

The growth of *M. aeruginosa* was evaluated by cells enumeration. The samples were diluted with Mill-Q water to obtain an appropriate cell density for microscopic counts. Then the samples were dripped to a hemocytometer and covered with a clear cover for counting. The enumeration was achieved by a microscope. To analyze the total MCs including intracellular MCs and the MCs in the solution, samples were filtered by glass microfiber filters to separate cells and MA media. Cells trapped by the filter were exposed to 5% acetic acid solution with shaking for 30 min to release the intracellular toxin. Microcystins in the acetic acid solution were absorbed by ODS column after filtration by 0.2 μm cellulose acetate filters. Then microcystins were dissolved in methanol for analysis by HPLC.

3.3 Results and discussion

3.3.1 Characterization of photocatalyst samples

Fig. 3.1 shows the absorption (100-reflectance) spectra for WO₃ and Pt/WO₃ powders. The absorption of WO₃ increased at approximately 460 nm, which is consistent with previously reported value [16]. For Pt/WO₃ sample, with the contribution of Pt doping the spectrum shows stronger broad absorption in the visible light region. The XRD patterns of WO₃ and Pt/WO₃ samples are illustrated in Fig. 3.2. Compared to tungsten oxide JCPD files (No. 43-1035) and those reported by others [23, 24], the diffraction patterns of the samples assigned those of WO₃ monoclinic structure.


As shown, no sign of crystallite Pt is detected in the patterns with Pt/WO₃. It can be related to the fact that lower Pt concentrations lie below XRD instrumental detection limit and indicated that the Pt doping did not influence the crystal structures of WO₃.

3.3.2 Photocatalytic inhibition of algal growth under solar light

Fig. 3.4 shows the results of photocatalytic inhibition of algal growth under solar light. After 6 days of irradiation, *M. aeruginosa* in the control samples kept growing and the number of algae cells increased from 1.3×10^6 to 2.2×10^6 . However, the growth of *M. aeruginosa* in the samples treated by photocatalyst was inhibited and the algae cells decreased from 1.3×10^6 to 0.1×10^6 . These results show that the photocatalytic treatment had the function of inactivation of microorganisms.

It is generally believed that the inactivation of microorganisms by

photocatalytic treatment is mainly due to oxidative radicals (mainly •OH) produced by photocatalyst irradiation [20]. When a photocatalyst is illuminated with a light of an appropriate wavelength, pairs of electrons (e⁻) and electron holes (h⁺) are generated on the surface of the catalyst by photons. These pairs react with oxygen and water molecules or hydroxyl groups adsorbed on the surface of the catalyst and form highly reactive oxygen species, such as hydroxyl radicals (•OH), which is expected to destroy the microorganisms [21]. The existence of Pt co-catalyst can promote O₂ reduction in a multi-electron process [17, 22].



3.3.3 Photocatalytic degradation of total MCs

Since the finally purpose of photocatalytic treatment is to reduce the MCs concentration in the wastewater, the total toxin concentration was analyzed in our experiment, the results were shown in Fig. 5. Without photocatalytic treatment, the total toxin concentration was increased from 624 to 741 µg/L during 6 days of irradiation. And with the existence of Pt/WO₃ photocatalyst, the total toxin concentration was decreased from 624 to 100µg/L after 6 days of photocatalytic treatment.

The protective cell structures of *M. aeruginosa* including the cell wall, the cell membrane and the organelle membranes were all destroyed by the oxidative species generated in photocatalytic process. During this process, the MCs were transferred from the inside of cells to the solution and further degraded by those oxidative species. These results further confirmed that Pt/WO₃ photocatalytic treatment is an environmental friendly way for the purification of wastewater containing algal toxin.

3.4 Conclusions

The photocatalytic inhibition of algal growth under solar light was investigated using *M. aeruginosa* as the model algae and Pt/WO₃ as the photocatalyst. The experiment results shows that the algal growth was successfully controlled by the Pt/WO₃ and the total MCs was also depredated to a low level.

The major problem in this treatment method is the recovery of the photocatalyst. Fortunately, a lot of works were already done for the immobilization of photocatalyst, such as magnetic recovery method and glass coating method. With appropriate immobilization technology, it can be sure that the photocatalytic treatment will be a promising way for in-situ control of cyanotoxins.

3.5 References

- [1] Chow CWK, House J, Velzeboer RMA, Drikas M, Burch MD, Steffensen DA, "The effect of ferric chloride flocculation on cyanobacterial cells," *Water Research*, Vol. 32, No. 3, 1998, pp. 808-814.
- [2] Mohamed ZA, "Accumulation of cyanobacterial hepatotoxins by daphnia in some egyptian irrigation canals," *Ecotoxicology and Environmental Safety*, Vol. 50, No. 1, 2001, pp. 4-8.
- [3] Warhurst AM, Raggett SL, McConnachie GL, Pollard SJT, Chipofya V, Codd GA, "Adsorption of the cyanobacterial hepatotoxin microcystin-LR by a low-cost activated carbon from the seed husks of the pan-tropical tree, *Moringa oleifera*," *Science of the Total Environment*, Vol. 207, No. 2-3, 1997, pp. 207-211.
- [4] Matsunaga T, Tomoda R, Nakajima T, Wake H, "Photoelectrochemical sterilization of microbial cells by semiconductor powders," *FEMS Microbiology Letters*, Vol. 29, No. 1-2, 1985, pp. 211-214.
- [5] Ibanez JA, Litter MI, Pizarro RA, "Photocatalytic bactericidal effect of TiO₂ on *Enterobacter cloacae*. Comparative study with other Gram (-) bacteria," *Journal of Photochemistry and Photobiology a-Chemistry*, Vol. 157, No. 1, 2003, pp. 81-85.
- [6] Chong MN, Jin B, Zhu H, Saint C, "Bacterial inactivation kinetics, regrowth and synergistic competition in a photocatalytic disinfection system using anatase titanate nanofiber catalyst," *Journal of Photochemistry and Photobiology A:*

Chemistry, Vol. 214, No. 1, 2010, pp. 1-9.

- [7] Kim B, Kim D, Cho D, Cho S, "Bactericidal effect of TiO₂ photocatalyst on selected food-borne pathogenic bacteria," *Chemosphere*, Vol. 52, No. 1, 2003, pp. 277-281.
- [8] Linkous CA, Carter GJ, Locuson DB, Ouellette AJ, Slattery DK, Smith LA, "Photocatalytic inhibition of algae growth using TiO₂, WO₃, and cocatalyst modifications," *Environmental Science & Technology*, Vol. 34, No. 22, 2000, pp. 4754-4758.
- [9] Peller JR, Whitman RL, Griffith S, Harris P, Peller C, Scalzitti J, "TiO₂ as a photocatalyst for control of the aquatic invasive alga, *Cladophora*, under natural and artificial light," *Journal of Photochemistry and Photobiology a-Chemistry*, Vol. 186, No. 2-3, 2007, pp. 212-217.
- [10] Zhao ZG, Miyauchi M, "Nanoporous-walled tungsten oxide nanotubes as highly active visible-light-driven photocatalysts," *Angewandte Chemie-International Edition*, Vol. 47, No. 37, 2008, pp. 7051-7055.
- [11] Sathish M, Viswanathan B, Viswanath RP, Gopinath CS, "Synthesis, characterization, electronic structure, and photocatalytic activity of nitrogen-doped TiO₂ nanocatalyst," *Chemistry of Materials*, Vol. 17, No. 25, 2005, pp. 6349-6353.
- [12] Xu JJ, Ao YH, Fu DG, "A novel Ce, C-codoped TiO₂ nanoparticles and its photocatalytic activity under visible light," *Applied Surface Science*, Vol. 256, No.

3, 2009, pp. 884-888.

- [13] Wu ZB, Dong F, Liu Y, Wang HQ, "Enhancement of the visible light photocatalytic performance of C-doped TiO₂ by loading with V₂O₅," *Catalysis Communications*, Vol. 11, No. 2, 2009, pp. 82-86.
- [14] Chatterjee D, Dasgupta S, "Visible light induced photocatalytic degradation of organic pollutants," *Journal of Photochemistry and Photobiology C-Photochemistry Reviews*, Vol. 6, No. 2-3, 2005, pp. 186-205.
- [15] Lin CF, Wu CH, Onn ZN, "Degradation of 4-chlorophenol in TiO₂, WO₃, SnO₂, TiO₂/WO₃ and TiO₂/SnO₂ systems," *Journal of Hazardous Materials*, Vol. 154, No. 1-3, 2008, pp. 1033-1039.
- [16] Abe R, Takami H, Murakami N, Ohtani B, "Pristine simple oxides as visible light driven photocatalysts: Highly efficient decomposition of organic compounds over platinum-loaded tungsten oxide," *Journal of the American Chemical Society*, Vol. 130, No. 25, 2008, pp. 7780-7781.
- [17] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Complete oxidation of acetaldehyde and toluene over a Pd/WO₃ photocatalyst under fluorescent- or visible-light irradiation," *Chemical Communications*, Vol. No. 43, 2008, pp. 5565-5567.
- [18] Arai T, Yanagida M, Konishi Y, Iwasaki Y, Sugihara H, Sayama K, "Promotion effect of CuO co-catalyst on WO₃-catalyzed photo degradation of organic substances," *Catalysis Communications*, Vol. 9, No. 6, 2008, pp. 1254-1258.

- [19] Abe R, Takami H, Murakami N, Ohtani B, "Pristine simple oxides as visible light driven photocatalysts: Highly efficient decomposition of organic compounds over platinum-loaded tungsten oxide," *Journal of the American Chemical Society*, Vol. 130, No. 25, 2008, pp. 7780-7781.
- [20] Rizzo L, "Inactivation and injury of total coliform bacteria after primary disinfection of drinking water by TiO₂ photocatalysis," *Journal of Hazardous Materials*, Vol. 165, No. 1-3, 2009, pp. 48-51.
- [21] Rajagopal G, Maruthamuthu S, Mohanan S, Palaniswamy N, "Biocidal effects of photocatalytic semiconductor TiO₂," *Colloids and Surfaces B-Biointerfaces*, Vol. 51, No. 2, 2006, pp. 107-111.
- [22] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Reaction Mechanism and Activity of WO₃-Catalyzed Photodegradation of Organic Substances Promoted by a CuO Cocatalyst," *Journal of Physical Chemistry C*, Vol. 113, No. 16, 2009, pp. 6602-6609.

Table 3.1 Composition of culture medium

Component	Concentration (L ⁻¹)
Ca(NO ₃) ₂ ·4H ₂ O	50 mg
KNO ₃	100 mg
NaNO ₃	50 mg
Na ₂ SO ₄	40 mg
MgCl ₂ ·4H ₂ O	50 mg
<i>β</i> -Na ₂ glycerophosphate	100 mg
Na ₂ EDTA	5 mg
FeCl ₃ ·6H ₂ O	0.5 mg
MnCl ₂ ·4H ₂ O	5 mg
ZnCl ₂	0.5 mg
CoCl ₂ ·6H ₂ O	5 mg
Na ₂ MoO ₄ ·2H ₂ O	0.8 mg
H ₃ BO ₃	20 mg
Bicine	500 mg




Fig. 3.1 Schematic diagram of the apparatus




Fig. 3.2 Absorption spectrum of (A) Pt/WO₃ and (B) Pure WO₃, respectively.




Fig. 3.3 XRD patterns of (A) pure WO_3 and (B) Pt/WO_3 , respectively.




Fig. 3.4. Photocatalytic inhibition of algal growth. Experimental conditions: Catalyst concentration of 150 mg/L and simulated solar light intensity of 0.8 mW/cm².




Fig. 3.5 Total MCs concentration during the photocatalytic inhibition of algal growth. Experimental conditions: Catalyst concentration of 150 mg/L and simulated solar light intensity of 0.8 mW/cm².

Chapter 4 Comparison of the performance between photocatalytic method and electrochemical method for the degradation of phenol

4.1 Introduction

Phenol and phenolic compounds are among the most prevalent forms of chemical pollutants and widely exist in polluted industrial wastewater in today's world. Phenol and its derivatives are widely used as raw materials and intermediates in many industries. So the Wastewater contained phenolic compounds mainly come from coking, oil refining, metallurgy, mechanical procession, glass-making, coal tar distillation, pharmaceuticals, etc [1]. Phenolic compounds cause acute toxicity, over 2mg/L phenol concentration is toxic to aquatic life and concentrations between 10 and 100mg/L can make them die within 96 h. The U.S. Environmental Protection Agency manifest that phenols represent a group of organics frequently found in various industrial effluents and reported in hazardous waste sites. Moreover according to the environmental protection rules of the Central Pollution Control Board (CPCB) the discharge limit of phenols in inland water is 1 mg/L.

Conventional wastewater treatment methods like flocculation, precipitation, adsorption on granular activated carbon, air stripping or reverse osmosis, combustion, and biological methods are incapable of removing many biorecalcitrant pollutants like phenols. This means that finding new efficient treatment methods became an imperative task.

In recent years, as one of the advanced oxidation technologies, photocatalytic oxidation has been extensively researched for the degradation and removal of highly toxic organic compounds in water purification. Among various semiconductors, titanium oxide (TiO_2), due to the excellent stability and high photoactivity under ultraviolet light, has been employed for both fundamental research and practical applications. Several researchers have studied the photocatalytic degradation of phenol in aerated suspensions of TiO_2 upon illumination with near-UV light [2, 3]. However, TiO_2 has a large absorption band gap (E_g) of 3.2 eV that restricts its universal use because it can only absorb UV light [4]. Conversely, with an E_g between 2.4 eV and 2.8 eV, tungsten oxide (WO_3) is a photocatalyst that absorbs visible light irradiation up to 480 nm [11]. Compared with mixed metal oxides and doped oxides, WO_3 is inexpensive to prepare and stable in acidic and oxidative conditions, which makes it a promising material for photocatalytic applications. Previous research showed that WO_3 degradation of organic species under visible light intensified in the presence of suitable co-catalysts, such as Pt, Pd and CuO [5-7]. From now on, there are few papers about degradation of phenol under visible light with WO_3 -based catalysts.

As another advanced oxidation technology, Electrochemistry method has also attracted many attentions because of the advantages of ease of control and environmental compatibility. A lot of research works had proven that Electrochemical oxidation method is effective for the treatment of various types of wastewater including the phenolic wastewater [8-12]. Electrochemical reaction can effectively

oxidize toxic organics [9, 12-14]. With unique features such as simplicity and robustness in structure and operation, it is possible that the electrochemical process can be developed as a cost-effective technology for the treatment of aromatic pollutants, particularly for low volume applications [11]. The materials of anodes play an important role in electrochemical [14, 15]. The current efficiency of traditional electrodes is very low in organic degradation, such as using graphite and nickel [16]. At present, dimensionally stable anodes (DSA), such as SnO₂, RuO₂ or IrO₂, have been widely used for the indirect oxidation of various organic pollutants [17]. In the course of indirect electro-oxidation, hydroxyl radicals, strong oxidants that are generated on the anodic surface, can degrade organic pollutants completely. However, because of the low •OH production at the anode, it is difficult to achieve the total mineralization [11, 18]. To increase the production of active species, NaCl has been used as a supporting electrolyte [17, 19], because hypochlorous acid (HClO) can form with hydrolysis of Cl₂ gas during electrolysis [20, 21].

The pursers of this research is to do a comparison of the performance between the two kind of advanced oxidation technologies, photocatalytic oxidation method and electrochemical oxidation method, for the degradation of phenol. The degradation parameters of each method were investigated and the advantages and disadvantages of each process were demonstrated.

4.2 Experiment

4.2.1 Experimental method for electrochemical degradation of phenol

In this research, the RuO₂/Ti electrode (TOHOTEC Co. Japan) was used as anode to degrade phenol. RuO₂ is a sort of widely used electrode covering material with strong ability of the evolution of chlorine and higher oxygen evolution potential while high oxygen evolution potential can reduce the losses of electric power and increase the current efficiency. A titanium plate (TOHOTEC Co. Japan) was used as the cathode.

The electrochemical cell was a 500ml beaker, the effective area of the electrode is 43cm², the distance between the electrodes was fixed at 3 cm, and a DC potentiostat was employed as power supply for electrochemical degradation. Below the beaker there is a magnetic stirrer to homogenize the solution.

An aliquot of phenol standard solution was added to the beaker to achieve an initial concentration of 10 mg/L. Different dosage of NaCl were added into the phenol solutions as the supporting electrolyte. The current densities were controlled by the DC potentiostat. At 20 min intervals, samples were drawn from the beaker for phenol analysis.

4.2.2 Experiment method for photocatalytic degradation of phenol

The photocatalyst used for phenol degradation was Pt/WO₃ which was prepared by a photo deposition method [18].

The reactor was a 6-mL vessel equipped with a magnetic stirrer. A solar lamp

(XC-100B, SERIC Ltd., Japan) was used as the irradiation source, and the light intensity was measured with a photometer (LI-250A, LI-COR Inc., USA). The photoemission spectrum was measured with an optical fiber spectrometer (USB4000, Ocean Optics Inc., USA).

An aliquot of phenol standard solution was added to the test solution to achieve an initial concentration of 10 mg/L. A suspension with catalyst particles was transferred to the reactor containing phenol to obtain a final volume of 5 ml. Before irradiation, the suspension was stirred for 60 min in the dark to equilibrate the solution. During irradiation, samples were taken and centrifuged every 30 minutes for analysis.

Phenol concentration was analyzed by HPLC.

4.3 Result and discussion

4.3.1 Effect of catalyst loading on photocatalytic degradation of phenol

For the investigation of catalyst loading, a series of experiments were carried out by varying the catalyst concentration from 100 to 300 mg/L. The degradation results are shown in Fig. 4.1. It can be seen from the figure that when catalyst loading ranged from 100 to 200mg/L, the photocatalytic degradation rate increase with the increase of catalyst concentration. But increasing the catalyst concentration to 300mg/L, the degradation rate decreased.

Many studies have reported that the rates of photocatalytic degradation for

organic pollutants are affected by the number of active sites and photon-absorption ability of the catalyst used. Many authors have investigated the reaction rate as a function of catalyst loading under different experimental conditions [22, 23]. Our results are in good agreement with reported values in the literature. Chen et al. has described the possible explanation for this behavior [24]. The increase of catalyst concentration means more photons could be absorbed on the surface of catalyst and more electron/hole pairs will be generated and thus improve the formation of OH radicals for photocatalytic degradation. This fact can be confirmed from catalyst loadings less than 200mg/L. However, when catalyst loading is further increased from 200 to 300 mg/L, the performance of the catalyst decrease. It is probably that at high catalyst concentration, the aggregation of catalyst could reduce the total active surface area available for adsorbing phenol and absorbing light radiation. On the other hand, a higher concentration of catalyst creates turbidity, which is capable of reducing the penetration intensity of light radiation by the scattering effect [25]. So the optimal amount of catalyst was 200mg/L in our experiment.

4.3.2 Effect of light intensity on photocatalytic degradation of phenol

Light intensity is an important factor in influencing photocatalytic activity and normally a linear relationship between destruction rate and light intensity when the light intensity is relatively low. The effect of the light intensity was investigated by varying light intensity from 0.2 to 1.2 mW/cm². Fig. 4 shows the *phenol degradation curves* for different solar light intensity.

As shown in Fig. 4.2, the rate of degradation of phenol was found to increase as

light intensity increased. With the catalyst loading constant, higher light intensity means more photons available on the catalyst surface and more reactive radicals will be generated to attack the phenol molecule. However, when light intensity increased from 0.8 mW/cm^2 to 1.2 mW/cm^2 , the removal rate was only enhanced slightly. The possible reason is that the number of available photons was limited to a certain amount of catalyst, when the light intensity was strong enough, more reactive species cannot be generated by increasing the light intensity. At the highest light intensity, 73% of phenol was removed in 3h of irradiation. Based on our experiment results, the optimized condition was 200mg/L of catalyst loading and 1.2 mW/cm^2 of light intensity.

4.3.3 Effect of NaCl on electrochemical degradation of phenol

Fig. 4.3 shows the performance of Ti/RuO₂-Pt for degradation of phenol under different dosage of NaCl. For comparison, 0.5g/L Na₂SO₄ was used as the supporting electrolyte when the NaCl was 0g/L. The concentration of phenol decreased with respect to treatment time. Without the existence of NaCl, the degradation of phenol was only 8% after 80min of electrolysis, which was similar with study of Li et al. [11], who found that with the Ti/RuO₂ and Pt anodes only 40% or less of the TOC was removed after a long treatment period achieved. The phenol removal increased with the increasing of NaCl dosages, 75% of phenol was removed after 80min of electrolysis with 0.3g/L NaCl, and 95% of phenol removal was achieved when the NaCl concentration was increased to 0.6g/L. However, increase the NaCl concentration to 0.9g/L, the phenol removal was only enhanced slightly, from 95% to

96%.

4.3.4 Mechanism of electrochemical oxidation of phenol

Comninellis has explained the mechanism of oxidation of organic matter at oxide anode (MO_x) [9]. In the liquid phase electrochemical oxidation, water is electrolyzed by anodic catalysis to produce adsorbed hydroxyl radicals, given as Eq. (4.1):





The adsorbed hydroxyl radicals may form chemisorbed active oxygen.



Meanwhile, the hydroxyl radicals will react with each other to form molecular oxygen to complete the electrolysis of the water molecules.



Organic matter (R) included in wastewater are oxidized by hydroxyl radicals



With the existence of chloride ions in the water, another strong oxidant of hypochlorite will be produced near the anode during the electrochemical process [17].



The organic matter (R) are also oxidized by hypochlorite [17]



From the results of our experiment, it can be seen that without the existence of NaCl, the degradation of phenol was only 8% after 80min of electrolysis. This phenomenon indicated that the amount of OH radicals generated by anodic catalysis

maybe not enough for the degradation of phenol. The main active species during the electrochemical degradation is the hypochlorite. However, increase the NaCl concentration to 0.9g/L, the phenol removal was only enhanced slightly, from 95% to 96%. This phenomenon could be explained by the fact that under a certain value of working current and initial concentration of phenol, the amount of chloride ions which can be used for electrochemical degradation is limited, an excessive dosage of chloride ion had no further promoting effect on phenol removal.

4.3.5 Effect of current density on electrochemical degradation of phenol

The effect of applied current density on electrochemical degradation of phenol is shown in Fig. 4.4. The phenol removal rate during electrolysis increased with increasing current density in the range of 20-50 mA/cm². At the current densities of 20 mA/cm², 30 mA/cm², 40 mA/cm² and 50 mA/cm², the phenol removal efficiency was 76%, 86%, 94% and 95% after 80min of electrolysis, respectively. As a higher current density enhances chlorine/hypochlorite production, more phenol is likely to be oxidized. However, higher current densities will also result in the release from solution of more Cl₂, which is harmful to human health. Moreover, this Cl₂ along with the O₂ generated by anodic side reaction formed many large gas bubbles which need to escape from solution during experiments. These big bubbles could disturb the mass transfer and contact interface between active substances and pollutants, and hence slow down the oxidation reaction [26]. This is the main reason why the apparent rate constant at 50mA/cm² was only slightly greater than that at

40 mA/cm². Based on our experiment results, the optimized condition was 0.6g/L NaCl and 40 mA/cm² of current density.

4.3.6 Comparison of the performance between photocatalytic method and electrochemical method

Fig. 4.5 shows the best performance under the optimized condition of each method. Complete removal of phenol was achieved by photocatalytic method through 8 hours while it only took 2 hours for electrochemical method to achieve complete removal of phenol.

According to the literatures, both Photocatalytic oxidation reaction and electrochemical oxidation reaction obeys a pseudo-first-order kinetic equation [27, 28] (Eq. 4.8).

$$\ln (C_0/C_t) = kt \quad (4.8)$$

where C_0 (mg/L) is the initial concentration of phenol, and C_t (mg/L) is the concentration of phenol over reaction time t (min).

The reaction constants (k) of each method are shown in Fig. 4.6. It is obvious that the reaction rate of electrochemical oxidation was much higher than that of Photocatalytic oxidation. From the experiment results we can find that for the degradation of phenol, the performance of electrochemical method was much better than the photocatalytic oxidation. But from the viewpoint of energy consumption, we can find that the two methods have their unique properties.

The main energy input of electrochemical method is the electricity power; the degradation performance can be easily enhanced by improving current density.

However, the cost of the energy consumption is also a big problem when considering the practical use. On the other hand, the main energy input of photocatalytic oxidation method is the light energy. Although the performance of photocatalytic oxidation can be enhanced by increasing the light intensity, it is not easy to control the light intensity when solar light is used as the light source.

Based on the above analysis, we come up with the conclusion that electrochemical method is appropriate for the treatment of high concentration organic wastewater. photocatalytic oxidation method is more appropriate for the in-situ control of refractory organics.

4.4 References

- [1] Lathasree S, Rao AN, SivaSankar B, Sadasivam V, Rengaraj K, "Heterogeneous photocatalytic mineralisation of phenols in aqueous solutions," *Journal of Molecular Catalysis A: Chemical*, Vol. 223, No. 1–2, 2004, pp. 101-105.
- [2] Kutty TRN, Ahuja S, "Retarding effect of surface hydroxylation on titanium(IV) oxide photocatalyst in the degradation of phenol," *Materials Research Bulletin*, Vol. 30, No. 2, 1995, pp. 233-241.
- [3] Chen D, Ray AK, "Photocatalytic kinetics of phenol and its derivatives over UV irradiated TiO₂," *Applied Catalysis B: Environmental*, Vol. 23, No. 2–3, 1999, pp. 143-157.
- [4] Zhao ZG, Miyauchi M, "Nanoporous-walled tungsten oxide nanotubes as highly active visible-light-driven photocatalysts," *Angewandte Chemie-International Edition*, Vol. 47, No. 37, 2008, pp. 7051-7055.
- [5] Abe R, Takami H, Murakami N, Ohtani B, "Pristine simple oxides as visible light driven photocatalysts: Highly efficient decomposition of organic compounds over platinum-loaded tungsten oxide," *Journal of the American Chemical Society*, Vol. 130, No. 25, 2008, pp. 7780-7781.
- [6] Arai T, Horiguchi M, Yanagida M, Gunji T, Sugihara H, Sayama K, "Complete oxidation of acetaldehyde and toluene over a Pd/WO₃ photocatalyst under fluorescent- or visible-light irradiation," *Chemical Communications*, Vol. No. 43,

2008, pp. 5565-5567.

- [7] Arai T, Yanagida M, Konishi Y, Iwasaki Y, Sugihara H, Sayama K, "Promotion effect of CuO co-catalyst on WO₃-catalyzed photo degradation of organic substances," *Catalysis Communications*, Vol. 9, No. 6, 2008, pp. 1254-1258.
- [8] Pulgarin C, Adler N, Peringer P, Comninellis C, "Electrochemical detoxification of a 1,4-benzoquinone solution in wastewater treatment," *Water Research*, Vol. 28, No. 4, 1994, pp. 887-893.
- [9] Christos C, "Electrocatalysis in the electrochemical conversion/combustion of organic pollutants for waste water treatment," *Electrochimica Acta*, Vol. 39, No. 11-12, 1994, pp. 1857-1862.
- [10] Vlyssides AG, Loizidou M, Karlis PK, Zorpas AA, Papaioannou D, "Electrochemical oxidation of a textile dye wastewater using a Pt/Ti electrode," *Journal of Hazardous Materials*, Vol. 70, No. 1-2, 1999, pp. 41-52.
- [11] Li X-y, Cui Y-h, Feng Y-j, Xie Z-m, Gu J-D, "Reaction pathways and mechanisms of the electrochemical degradation of phenol on different electrodes," *Water Research*, Vol. 39, No. 10, 2005, pp. 1972-1981.
- [12] Brillas E, Calpe JC, Casado J, "Mineralization of 2,4-D by advanced electrochemical oxidation processes," *Water Research*, Vol. 34, No. 8, 2000, pp. 2253-2262.
- [13] Kötz R, Stucki S, Carcer B, "Electrochemical waste water treatment using high

overvoltage anodes. Part I: Physical and electrochemical properties of SnO₂ anodes " *Journal of Applied Electrochemistry*, Vol. 21, No. 1, 1991, pp. 14-20.

- [14] Feng YJ, Li XY, "Electro-catalytic oxidation of phenol on several metal-oxide electrodes in aqueous solution," *Water Research*, Vol. 37, No. 10, 2003, pp. 2399-2407.
- [15] Stucki S, Kötzt R, Carcer B, Suter W, "Electrochemical waste water treatment using high overvoltage anodes Part II: Anode performance and applications," *Journal of Applied Electrochemistry*, Vol. 21, No. 2, 1991, pp. 99-104.
- [16] Rodgers JD, Jedral W, Bunce NJ, "Electrochemical Oxidation of Chlorinated Phenols," *Environmental Science & Technology*, Vol. 33, No. 9, 1999, pp. 1453-1457.
- [17] Comminellis C, Nerini A, "Anodic oxidation of phenol in the presence of NaCl for wastewater treatment," *Journal of Applied Electrochemistry*, Vol. 25, No. 1, 1995, pp. 23-28.
- [18] Houk LL, Johnson SK, Feng J, Houk RS, Johnson DC, "Electrochemical incineration of benzoquinone in aqueous media using a quaternary metal oxide electrode in the absence of a soluble supporting electrolyte," *Journal of Applied Electrochemistry*, Vol. 28, No. 11, 1998, pp. 1167-1177.
- [19] Li M, Feng C, Hu W, Zhang Z, Sugiura N, "Electrochemical degradation of phenol using electrodes of Ti/RuO₂-Pt and Ti/IrO₂-Pt," *Journal of Hazardous Materials*, Vol. 162, No. 1, 2009, pp. 455-462.

- [20] Rajkumar D, Palanivelu K, "Electrochemical treatment of industrial wastewater," *Journal of Hazardous Materials*, Vol. 113, No. 1–3, 2004, pp. 123-129.
- [21] Bonfatti F, De Battisti A, Ferro S, Lodi G, Osti S, "Anodic mineralization of organic substrates in chloride-containing aqueous media," *Electrochimica Acta*, Vol. 46, No. 2–3, 2000, pp. 305-314.
- [22] Ralph W M, "Purification of water with near—u.v. illuminated suspensions of titanium dioxide," *Water Research*, Vol. 24, No. 5, 1990, pp. 653-660.
- [23] Mengyue Z, Shifu C, Yaowu T, "Photocatalytic degradation of organophosphorus pesticides using thin films of TiO₂," *Journal of Chemical Technology & Biotechnology*, Vol. 64, No. 4, 1995, pp. 339-344.
- [24] Chen JR, Xu XW, Lee AS, Yen TF, "A feasibility study of dechlorination of chloroform in water by ultrasound in the presence of hydrogen peroxide," *Environmental Technology*, Vol. 11, No. 9, 1990, pp. 829-836.
- [25] Neppolian B, Choi HC, Sakthivel S, Arabindoo B, Murugesan V, "Solar light induced and TiO₂ assisted degradation of textile dye reactive blue 4," *Chemosphere*, Vol. 46, No. 8, 2002, pp. 1173-1181.
- [26] An T, Zhang W, Xiao X, Sheng G, Fu J, Zhu X, "Photoelectrocatalytic degradation of quinoline with a novel three-dimensional electrode-packed bed photocatalytic reactor," *Journal of Photochemistry and Photobiology A: Chemistry*, Vol. 161, No. 2–3, 2004, pp. 233-242.

- [27] Xue Q, Li M, Shimizu K, Utsumi M, Zhang Z, Feng C, Gao Y, Sugiura N, "Electrochemical degradation of geosmin using electrode of Ti/IrO₂-Pt," *Desalination*, Vol. 265, No. 1-3, 2011, pp. 135-139.
- [28] Liu Y, Ohko Y, Zhang R, Yang Y, Zhang Z, "Degradation of malachite green on Pd/WO₃ photocatalysts under simulated solar light," *Journal of Hazardous Materials*, Vol. 184, No. 1-3, 2010, pp. 386-391.




Fig. 4.1 The effect of catalyst loading on the efficiency of photocatalytic degradation of phenol. Experimental conditions: phenol concentration of 10 mg/L, simulated solar light intensity of 0.4 mW/cm².




Fig. 4.2 The effect of light intensity on the efficiency of photocatalytic degradation of phenol. Experimental conditions: phenol concentration of 10 mg/L, catalyst loading of 200mg/L




Fig. 4.3 The effect of NaCl concentration on the efficiency of electrochemical degradation of phenol. Experimental conditions: phenol concentration of 10 mg/L, current density of 40mA/cm²




Fig. 4.4 The effect of current density on the efficiency of electrochemical degradation of phenol. Experimental conditions: phenol concentration of 10 mg/L, NaCl concentration of 0.6g/L




Fig. 4.5 Comparison of the performance between photocatalytic method and electrochemical method. Experimental conditions of electrochemical method: phenol concentration of 10 mg/L, NaCl concentration of 0.6g/L and current density of 40mA/cm². Experimental conditions of photocatalytic method: phenol concentration of 10 mg/L, catalyst loading of 200mg/L and simulated solar light intensity of 1.2 mW/cm².




Fig. 4.6 kinetics study of photocatalytic method and electrochemical method.

Experimental conditions of electrochemical method: phenol concentration of 10 mg/L, NaCl concentration of 0.6g/L and current density of 40mA/cm². Experimental conditions of photocatalytic method: phenol concentration of 10 mg/L, catalyst loading of 200mg/L and simulated solar light intensity of 1.2 mW/cm².

Chapter 5 Conclusions

This research mainly investigated the application of photocatalytic purification of water under solar light irradiation through 3 aspects. The first is the degradation of cyanotoxins, microcystin-LR (MC-LR), on three kinds of WO_3 -based photocatalysts under simulated solar light. It was found in this study that pure WO_3 shows low activity for MC-LR degradation due to its much positive conduction band level. Among three kinds of WO_3 -based photocatalysts, Pt/WO_3 shows the best performance for the degradation. Specifically, 1 mg/L of MC-LR was removed after 3 h of irradiation by 100 mg/L of Pt/WO_3 . With the existence of co-catalyst like Pd and Pt, the photocatalytic activity of WO_3 can be enhanced through the multiple-electron reduction of oxygen. The detection of proved that the solution of Pt/WO_3 generated the most amount of OH radical. Photocatalytic efficiency is affected by the initial pH of the solution, a neutral pH, such as a pH of 6, improved the efficacy of toxin removal. Analysis of reaction kinetics indicated that photocatalytic MC-LR degradation followed pseudo-first-order reaction kinetics, and the reaction rate increased with an increase in light intensity. Investigation of the effect of coexistent ions on the photocatalytic oxidation of MC-LR indicated that Cl^- could enhance the MC-LR degradation at concentrations lower than 0.02 mM and inhibit degradation at concentrations of 0.1 mM and 0.2 mM. The presence of Cu^{2+} or Fe^{3+} can improve MC-LR removal. This treatment method is a promising method for enhancing the treatment of refractory organic compounds.

To further diminish the cyanotoxins to a lower level, it is necessary to control the

growth of cyanobacteria. The second aspect is the photocatalytic inhibition of algal growth under solar light was investigated using *M. aeruginosa* as the model algae and Pt/WO₃ as the photocatalyst. The experiment results shows that the algal growth was successfully controlled by the Pt/WO₃ and the total MCs was also depredated to a low level.

The major problem in this treatment method is the recovery of the photocatalyst. Fortunately, a lot of works were already done for the immobilization of photocatalyst, such as magnetic recovery method and glass coating method. With appropriate immobilization technology, it can be sure that the photocatalytic treatment will be a promising way for in-situ control of cyanotoxins.

For further investigating photocatalytic technology in the field of refractory organic wastewater treatment, another advanced oxidation technology, electrochemical method was chosen for the comparison. In the third aspect, the comparison between photocatalytic method and electrochemical method was investigated through the degradation of phenol. It is obvious that the reaction rate of electrochemical oxidation was much higher than that of photocatalytic oxidation. From the experiment results we can found that for the degradation of phenol, the performance of electrochemical method was much better than the photocatalytic oxidation. But from the viewpoint of energy consumption, we can find that the two methods have their unique properties.

The main energy input of electrochemical method is the electricity power; the degradation performance can be easily enhanced by improving current density.

However, the cost of the energy consumption is also a big problem when considering the practical use. On the other hand, the main energy input of photocatalytic oxidation method is the light energy. Although the performance of photocatalytic oxidation can be enhanced by increasing the light intensity, it is not easy to control the light intensity when solar light is used as the light source.

Based on the above analysis, we come up with the conclusion that electrochemical method is appropriate for the treatment of high concentration organic wastewater. Photocatalytic oxidation method is more appropriate for the in-situ control of refractory organics.

In summary, the modified WO_3 nanoparticles have been successfully prepared and their photocatalytic activity for the degradation of organic toxins and refractory organic compounds and the inhibition effect in the growth of cyanobacteria were investigated. The results indicate that WO_3 can act as a promising material for solar-light driven photocatalytic technology.

Acknowledgements

My deepest gratitude goes first and foremost to Professor Zhenya Zhang, my supervisor, for his constant encouragement and guidance. He has helped me through all the stages of my Ph.D studies in the University of Tsukuba. Without his consistent and illuminating instruction, I could not finish my Ph.D studies. Second, I would like to express my heartfelt gratitude to the other academic advisor, Professor Norio Sugiura and Associate Professor Yingnan Yang for their kind encouragement, patient instructions and their precious suggestions for my study. Additionally, I wish to express my sincere appreciation to Dr. Yonggang Liu, for his instructive advice for my research plan and his selfless help.

Professors Norio Sugiura, Yoshiro Higano, Zhenya Zhang and Yingnan Yang are gratefully acknowledged for their efforts in review my graduation thesis.

Special gratitude is expressed to Professor Chuanping Feng, China University of Geosciences, Beijing, China, who led me into the field of water treatment and gave me the precious chance to study in the University of Tsukuba.

I should give my hearty thanks to all my lab mates and friends, Rongzhi Chen, Nan Chen, Xu Guo, Shengjiong Yang and many others for their genuine help in doing my experiment and made me work and study in a friendly environment

Finally, I should like to express my gratitude to my beloved parents who have always been helping me out of difficulties and supporting without a word of complaint.