



Coherent phonon study of (GeTe) | (Sb₂Te₃) m interfacial phase change memory materials

Kotaro Makino, Yuta Saito, Paul Fons, Alexander V. Kolobov, Takashi Nakano, Junji Tominaga, and Muneaki Hase

Citation: *Applied Physics Letters* **105**, 151902 (2014); doi: 10.1063/1.4897997

View online: <http://dx.doi.org/10.1063/1.4897997>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/apl/105/15?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

[Uniform Ti-doped Sb₂Te₃ materials for high-speed phase change memory applications](#)

Appl. Phys. Lett. **104**, 053119 (2014); 10.1063/1.4863430

[Comparison of thermal stabilities between Ge-Sb-Te and In-Sb-Te phase change materials](#)

Appl. Phys. Lett. **103**, 121906 (2013); 10.1063/1.4821855

[Hybrid density functional study of electronic and optical properties of phase change memory material: Ge₂Sb₂Te₅](#)

J. Appl. Phys. **113**, 033510 (2013); 10.1063/1.4775715

[Phase change behaviors of Zn-doped Ge₂Sb₂Te₅ films](#)

Appl. Phys. Lett. **101**, 051906 (2012); 10.1063/1.4742144

[A comparative study on electrical transport properties of thin films of Ge₁Sb₂Te₄ and Ge₂Sb₂Te₅ phase-change materials](#)

J. Appl. Phys. **110**, 013703 (2011); 10.1063/1.3603016

Over **600** Multiphysics Simulation Projects

[VIEW NOW >>](#)

COMSOL

The advertisement features a 3D simulation of a mechanical part with a red-to-blue color gradient representing a stress or temperature field. The text 'Over 600 Multiphysics Simulation Projects' is prominently displayed in white and blue. A blue button with white text says 'VIEW NOW >>'. The COMSOL logo is in the bottom right corner.

Coherent phonon study of $(\text{GeTe})_l(\text{Sb}_2\text{Te}_3)_m$ interfacial phase change memory materials

Kotaro Makino,^{1,a)} Yuta Saito,¹ Paul Fons,¹ Alexander V. Kolobov,¹ Takashi Nakano,¹ Junji Tominaga,¹ and Muneaki Hase²

¹Nanoelectronics Research Institute, National Institute of Advanced Industrial Science and Technology (AIST), Tsukuba Central 4, 1-1-1 Higashi, Tsukuba 305-8562, Japan

²Institute of Applied Physics, University of Tsukuba, 1-1-1 Tennodai, Tsukuba 305-8573, Japan

(Received 10 August 2014; accepted 30 September 2014; published online 13 October 2014)

The time-resolved reflectivity measurements were carried out on the interfacial phase change memory (iPCM) materials $[(\text{GeTe})_2(\text{Sb}_2\text{Te}_3)_4]_8$ and $[(\text{GeTe})_2(\text{Sb}_2\text{Te}_3)_{11}]_{20}$ as well as conventional $\text{Ge}_2\text{Sb}_2\text{Te}_5$ alloy at room temperature and above the RESET-SET phase transition temperature. In the high-temperature phase, coherent phonons were clearly observed in the iPCM samples while drastic attenuation of coherent phonons was induced in the alloy. This difference strongly suggests the atomic rearrangement during the phase transition in iPCMs is much smaller than that in the alloy. These results are consistent with the unique phase transition model in which a quasi-one-dimensional displacement of Ge atoms occurs for iPCMs and a conventional amorphous-crystalline phase transition takes place for the alloy. © 2014 AIP Publishing LLC. [<http://dx.doi.org/10.1063/1.4897997>]

Phase change memory (PCM) technology is now growing in importance and is being utilized for applications in nonvolatile electrical memories as well as in optical disks.¹ Pseudobinary chalcogenide alloys along the $\text{GeTe-Sb}_2\text{Te}_3$ tie-line such as $\text{Ge}_2\text{Sb}_2\text{Te}_5$ (GST) are commonly used because they exhibit large changes in optical and electrical properties between amorphous and crystalline phases. Superlattice-like structured GST, sometimes referred to as interfacial phase change memory (iPCM), consisting of GeTe and Sb_2Te_3 sub-layers has received considerable attention since the SET-RESET phase switching energy in iPCM was demonstrated to be far smaller than that in conventional GST alloys.² Additionally, huge magnetoresistance⁴ and anomalous magneto-optical Kerr-rotation⁵ stemming from the topological nature of the iPCM structure³ has been reported. The combination of electrical memory switching and the unusual topological nature of iPCM is expected to pave the way to a new class of memory technology.

iPCM films have the structure of $[(\text{GeTe})_l(\text{Sb}_2\text{Te}_3)_m]_n$, where l and m indicate the number of monolayers of each respective material, and n is a integer that represents the number of combined sub-layers. The phase transition is induced by a nanosecond electrical pulse. Figure 1(a) shows the primitive cell models for the high-resistance RESET and low-resistance SET states for the iPCM structure. In iPCM, the RESET-SET operation is thought to be governed by a quasi one-dimensional transition of Ge atoms at the interfaces between tetrahedrally coordinated sites and octahedrally coordinated sites without melting and it is thereby considered that this mechanism should be different from that in conventional GST alloys where an amorphous-crystalline phase transition plays a dominant role.¹ Spectroscopic measurements of lattice vibration therefore can serve as a

powerful tool to elucidate the difference in phase transition mechanisms between iPCM and conventional GST alloys.

Herein, we report on optical pump-probe coherent phonon spectroscopy performed on iPCMs with a femtosecond laser to obtain a new perspective on the thermally induced phase transition mechanism as indicated by the observed differences in the coherent phonons associated with the phase transition. Ultrafast laser pulses absorbed in an opaque material excite Raman active coherent phonons via impulsive stimulated Raman scattering processes⁶ or abrupt changes in lattice potentials.⁷ Coherent phonons can be detected by time-resolved optical reflectivity measurement as a change




FIG. 1. Structural models of (a) the $\{2,1\}$ -iPCM in the RESET and (b) SET states. The green, purple, and orange balls indicate Ge, Sb, and Te atoms, respectively.

^{a)}Electronic mail: k-makino@aist.go.jp

in reflectivity with the time periods of coherent phonons. Coherent phonon spectroscopy provides good sensitivity for low frequency optical phonon modes ($<200\text{ cm}^{-1}$) which are dominant in GST materials⁸ and has been applied so far to GST materials to unveil their lattice dynamics, which is important for the understanding of the phase transition process.^{9–14} For example, the amorphous GST alloy transforms into the fcc crystalline state or the hcp crystalline state depending on the annealing temperature.¹⁵ It was found that a drastic change in coherent phonon spectra is induced by a thermally induced phase transition.⁹

We investigated two different iPCM structures. The first was $[(\text{GeTe})_2(\text{Sb}_2\text{Te}_3)_4]_8$ (hereafter referred to as {2,4}-iPCM) and the second was $[(\text{GeTe})_2(\text{Sb}_2\text{Te}_3)_1]_{20}$ ({2,1}-iPCM). Both films were deposited on Si (100) substrates using a helicon-wave sputtering system. Note that the layer thickness and, more importantly, the structures of the iPCM samples currently investigated are different from those of previously investigated samples by coherent phonon spectroscopy.^{10–12} The {2,4}-iPCM sample is composed of 1.0 nm GeTe sub-layers and 4.0 nm Sb_2Te_3 sub-layers and the {2,1}-iPCM sample consists of 1.0 nm GeTe sub-layers and 1.0 nm Sb_2Te_3 sub-layers on a 5 nm-thick Sb_2Te_3 growth controlling layer.¹⁶ The total film thicknesses of the two iPCMs structures were nearly identical. The as-deposited amorphous GST alloy film that was used for comparison was fabricated by co-sputtering of GeTe and Sb_2Te_3 on a Si substrate using RF magnetron sputtering. A 20-nm thick optically transparent ZnS-SiO₂ layer was deposited on top of all samples to prevent oxidation. In the iPCM samples, the phase transition temperature from the RESET to SET state is $\simeq 170^\circ\text{C}$ and the electrical resistance reversibly changes with temperature.⁵ The alloy shows irreversible phase change, namely, the amorphous GST alloy transforms into an fcc phase at $\simeq 150^\circ\text{C}$ which further transforms into a hcp phase at $\simeq 210^\circ\text{C}$.⁹ After crystallization, subsequent cooling of the alloy does not affect its phase as evidenced by the results of a temperature-dependent resistance measurement.¹⁵ Thus, the crystalline phase can be “locked in” by suitable heating.

Time-resolved pump-probe reflectivity measurements were carried out utilizing a near-infrared optical pulse of 20 fs duration and a center wavelength of 830 nm derived from a Ti:sapphire laser oscillator. The linearly polarized pump (s-polarized) and probe (p-polarized) pulses were focused with a lens ($f = 100\text{ mm}$) onto the sample (held on a hot plate) at $\simeq 45^\circ$ and $\simeq 50^\circ$ with respect to the sample normal, respectively. The fluence of the pump pulse was kept below $100\ \mu\text{J}/\text{cm}^2$ so that the increase in the sample temperature due to laser irradiation could be neglected. The transient reflectivity change of the probe pulse ($\Delta R/R$) was recorded as a function of the pump-probe time delay. The majority of the transient electronic response was subtracted by a band pass filter within the current amplifier.

Figure 2 shows the $\Delta R/R$ signals as a function of the pump-probe time delay for the two iPCM samples and the GST alloy sample obtained at 25°C and 180°C . At 25°C , oscillations due to coherent phonons superimposed on the nonoscillatory electronic response were clearly observed in all samples. The most noticeable difference between the




FIG. 2. Time-resolved $\Delta R/R$ signals in (a) {2,4}-iPCM, (b) {2,1}-iPCM, and (c) GST alloy samples observed at 25°C and 180°C .

iPCMs and the alloy is that the oscillations associated with coherent phonons survive even at 180°C in the iPCM samples while the amplitude of coherent phonon oscillations is strongly attenuated in the alloy sample at the same temperature. After cooling the samples down to 25°C , further differences were observed (not shown) as follows. In the alloy sample, the oscillation amplitude did not recover. For the iPCM samples, on the contrary, the intensity of oscillation largely recovered. The lifetime of the oscillation observed in the {2,4}-iPCM sample was noticeably longer than that in the other samples as discussed later.

Fourier transform (FT) spectra were obtained from the $\Delta R/R$ signals for the iPCM samples and the GST alloy sample. Figures 3(a) and 3(b) show FT spectra obtained for the {2,4}- and {2,1}-iPCM samples, respectively. At 25°C , two dominant peaks were observed at around 3.4 THz (3.40 THz for the {2,4}-iPCM and 3.36 THz for the {2,1}-iPCM) and at around 5 THz (5.07 THz for the {2,4}-iPCM and 4.82 THz for the {2,1}-iPCM) in both samples. Hereafter, for convenience, we refer to the two dominant peaks as the 3.4 THz mode and the 5 THz mode, respectively. In addition, a small peak was observed at 2.11 THz only in the {2,4}-iPCM sample and a shoulder peak was seen at 3.78 THz in the {2,1}-iPCM sample. Upon heating the iPCM samples above the phase transition temperature, the FT intensity drops but partially recovers after cooling to 25°C . For the {2,4}-iPCM sample, the 5 THz peak shifted from 5.07 THz to 4.99 THz upon heating, and finally recovered to 5.07 THz after cooling. The {2,1}-iPCM sample shows a similar yet more ambiguous trend due to the broad peak width and a small shift. No significant shift of the other mode was confirmed.




FIG. 3. FT spectra for (a) {2,4}-iPCM, (b) {2,1}-iPCM and (c) GST alloy films obtained from $\Delta R/R$ data taken at 25 °C before heating, at 180 °C, and 25 °C after cooling. The black inverted triangle in (b) indicates the position of the shoulder peak at 3.78 THz.

As shown in Fig. 3(c), two main peaks were observed at 3.72 THz and 4.75 THz before heating the GST alloy. The intensity of both peaks was drastically suppressed upon heating and the position of the phonon peaks become unclear due to the electronic-origin background superimposed on the phonon peaks. Subsequent cooling increased the low frequency electronic background, yet the change in the phonon intensity was negligible. In order to remove the background, the derivative of the $\Delta R/R$ signal was taken and its FT spectra revealed that two main peaks appear at around 3.65 THz and 5.03 THz at 180 °C (not shown). These results suggest that the amorphous alloy sample transformed into the fcc crystalline state upon heating and the crystalline state remain virtually unchanged upon cooling, although there are some minor difference in the spectral shape from the previous report.⁹

For the case of the GST alloy, the phase transition can be understood in the framework of a general amorphous-crystalline phase transition caused by thermal processes that include crystal growth for crystallization and a melt-quench process for amorphization, although several underlying mechanisms have been proposed.^{17–19} In the current measurements, the amorphous GST alloy transformed into the fcc crystalline state after heating and the crystalline structure was preserved after cooling. In contrast, the phase transition mechanism in iPCMs is thought to be different from that in the alloy. iPCM was named after its unique phase transition mechanism that arises at the interfaces between sub-layers.² Therefore, the clear contrast in the behavior of coherent phonons upon heating between iPCMs and GST alloy can be

reasonably attributed to the difference in the phase transition mechanism. The change in the coherent phonon spectra for the iPCM films is much smaller than that for the GST alloy. This result strongly suggests that the rearrangement of atoms during the phase transition is small in iPCMs compared to GST alloy as can be expected from the phase transition model. In cooling the heated samples, a large part of the FT intensity recovers in the iPCM films but only a small change was observed in the GST alloy upon cooling as an irreversible phase transition occurred.¹⁵ Thus, the structural change in iPCMs associated with temperature on relatively slow time scales is reversible and consistent with the previous result of resistivity measurements.⁵ The incomplete recovery of the FT intensity can be explained by annealing effects which generally arise in PCM. It should be noted that the thermal phase transition may be different from the electrical RESET-SET operation² because the electrical phase transition is much faster (ns range) than the present heater-induced quasi-static phase transition. This is an area for further research.

Based on the previous reports on GST materials⁹ and $\text{Bi}_2\text{Te}_3/\text{Sb}_2\text{Te}_3$ superlattices,²⁰ the A_{1g} mode in Sb_2Te_3 sub-layers is a candidate for the lowest frequency mode found in the {2,4}-iPCM sample at 2.11 THz. This mode also exists in the Sb_2Te_3 crystalline phase^{21,22} and hence the appearance of this mode suggests a bulk-like structure for the Sb_2Te_3 sub-layers in the {2,4}-iPCM sample. Similarly, the 5 THz mode can be reasonably attributed to an additional A_{1g} mode in the Sb_2Te_3 sub-layers. With respect to remaining modes around 3.4 and 3.8 THz, the A_1 mode from the GeTe sub-layers are indicated in previous reports on other GST materials.^{9,11,13,14} It is worth mentioning that even for an epitaxial $\text{Ge}_2\text{Sb}_2\text{Te}_5$ film fabricated on a GaSb(001) substrate, the symmetry of crystal is distorted to some extent due to intrinsically existing vacancies and it was found by extensive investigation of coherent phonons that the symmetry of phonon modes was significantly modified as a result of the imperfect crystal structure.¹⁴ Polycrystalline samples can be expected to show more ambiguous phonon properties than an epitaxial sample.

Compared with the oscillatory pattern observed in the {2,1}-iPCM, the spectra of the {2,4}-iPCM possesses a long life time. To clarify the decay time scale of the coherent phonons, we applied a wavelet transformation to carry out a time-frequency analysis²³ of the $\Delta R/R$ signals measured on the pristine samples. Figure 4 compares the wavelet spectrograms for the two iPCMs. Here, the electronic background was subtracted by a combination of exponential functions. As shown in Fig. 4(a), the origin of the relatively long phonon lifetime in {2,4}-iPCM sample is found to be the 5 THz mode which assigned to the A_{1g} mode in the Sb_2Te_3 sub-layers as mentioned above. Since the {2,4}-iPCM sample has thicker Sb_2Te_3 sub-layers than the other samples, the structure of this layer should be more bulk-like as evidenced by the appearance of the 2.11 THz mode. Hence, we attributed the relatively long lifetime of the 5 THz mode to the small lattice deformation of the Sb_2Te_3 sub-layers with a small phonon scattering rate. Note that the thicker Sb_2Te_3 sub-layers in the {2,4}-iPCM versus the {2,1}-iPCM are expected to serve to stabilize and orient the GeTe sub-layer




FIG. 4. Wavelet transform spectrograms for (a) {2,4}-iPCM and (b) {2,1}-iPCM calculated from $\Delta R/R$ signals taken at 25 °C before heating. The white dotted lines are guides for the eye.

and the current result is consistent with this supposition. On the other hand, the 3.4 THz mode may be localized in the GeTe sub-layer or at the GeTe/Sb₂Te₃ interface because no Sb₂Te₃ sub-layer thickness dependence was found for this mode. Also, other contributory factors such as scattering processes in the interfaces²⁰ and anharmonic phonon-phonon interactions¹¹ should also be taken into consideration.

In conclusion, we have carried out coherent phonon spectroscopy on [(GeTe)₂(Sb₂Te₃)₄]₈ and [(GeTe)₂(Sb₂Te₃)₁]₂₀ films which are the dominant structure for iPCM applications and a conventional Ge₂Sb₂Te₅ alloy. At 25 °C, coherent phonon signals were clearly observed in all three samples. By increasing the sample temperature up to 180 °C, a large part of the coherent phonon signals were still observed in the iPCM samples although a RESET-to-SET phase transition was induced. In contrast, a significant suppression of coherent phonons was found for the case of the alloy sample at the same temperature due to a phase transition from the amorphous state to the fcc crystalline state. Upon subsequent cooling of the samples, it was found that the attenuation of coherent phonons introduced by heating was largely reversible in iPCMs while that in GST alloy was irreversible. These

temperature-induced significant differences originate from the small atomic rearrangements associated with the RESET-SET phase transition process in iPCMs. In addition, the results of a wavelet analysis applied to the $\Delta R/R$ signals for two different iPCMs revealed the differences in the structure of Sb₂Te₃ sub-layers which is related to the orientation and stability of the iPCM structure. These features are directly relevant to the future high-performance PCM technology.

This work was supported in part by KAKENHI-26790063 from MEXT, Japan. We acknowledge R. Kondou for sample preparation.

- ¹M. Wuttig and N. Yamada, *Nat. Mater.* **6**, 824 (2007).
- ²R. E. Simpson, P. Fons, A. V. Kolobov, T. Fukaya, M. Krbal, T. Yagi, and J. Tominaga, *Nat. Nanotechnol.* **6**, 501 (2011).
- ³J. Tominaga, A. V. Kolobov, P. Fons, T. Nakano, and S. Murakami, *Adv. Mater. Interfaces* **1**, 1300027 (2014).
- ⁴J. Tominaga, R. E. Simpson, P. Fons, and A. V. Kolobov, *Appl. Phys. Lett.* **99**, 152105 (2011).
- ⁵D. Bang, H. Awano, J. Tominaga, A. V. Kolobov, P. Fons, Y. Saito, K. Makino, T. Nakano, M. Hase, Y. Takagaki, A. Giussani, R. Calarco, and S. Murakami, *Sci. Rep.* **4**, 5727 (2014).
- ⁶R. Merlin, *Solid State Commun.* **102**, 207 (1997).
- ⁷H. J. Zeiger, J. Vidal, T. K. Cheng, E. P. Ippen, G. Dresselhaus, and M. S. Dresselhaus, *Phys. Rev. B* **45**, 768 (1992).
- ⁸G. C. Sosso, S. Caravati, C. Gatti, S. Assoni, and M. Bernasconi, *J. Phys.: Condens. Matter* **21**, 245401 (2009).
- ⁹M. Först, T. Dekorsy, C. Trappe, M. Laurenzis, H. Kurz, and B. Bechevet, *Appl. Phys. Lett.* **77**, 1964 (2000).
- ¹⁰K. Makino, J. Tominaga, and M. Hase, *Opt. Express* **19**, 1260 (2011).
- ¹¹M. Hase, Y. Miyamoto, and J. Tominaga, *Phys. Rev. B* **79**, 174112 (2009).
- ¹²K. Makino, J. Tominaga, A. V. Kolobov, P. Fons, and M. Hase, *Appl. Phys. Lett.* **101**, 232101 (2012).
- ¹³J. Hernandez-Rueda, A. Savoia, W. Gawelda, J. Solis, B. Mansart, D. Boschetto, and J. Siegel, *Appl. Phys. Lett.* **98**, 251906 (2011).
- ¹⁴A. Shalini, Y. Liu, U. A. S. Al-Jarah, G. P. Srivastava, C. D. Wright, F. Katmis, W. Braun, and R. J. Hicken, *Sci. Rep.* **3**, 2965 (2013).
- ¹⁵T. Siegrist, P. Jost, H. Volker, M. Woda, P. Merkelbach, C. Schlockermann, and M. Wuttig, *Nat. Mater.* **10**, 202 (2011).
- ¹⁶R. E. Simpson, P. Fons, A. V. Kolobov, M. Krbal, and J. Tominaga, *Appl. Phys. Lett.* **100**, 021911 (2012).
- ¹⁷A. V. Kolobov, P. Fons, A. I. Frenkel, A. L. Ankudinov, J. Tominaga, and T. Uruga, *Nat. Mater.* **3**, 703 (2004).
- ¹⁸K. Shportko, S. Kremers, M. Woda, D. Lencer, J. Robertson, and M. Wuttig, *Nat. Mater.* **7**, 653 (2008).
- ¹⁹B. Huang and J. Robertson, *Phys. Rev. B* **81**, 081204(R) (2010).
- ²⁰Y. Wang, X. Xu, and R. Venkatasubramanian, *Appl. Phys. Lett.* **93**, 113114 (2008).
- ²¹W. Richter and C. R. Beckerl, *Phys. Status Solidi B* **84**, 619 (1977).
- ²²G. C. Sosso, S. Caravati, and M. Bernasconi, *J. Phys.: Condens. Matter* **21**, 095410 (2009).
- ²³M. Hase, M. Kitajima, A. M. Constantinescu, and H. Petek, *Nature* **426**, 51 (2003).